

MLC Capacitors

Standard range - 10Vdc to 12kVdc

ProtectiCap™ capacitors

TCC/VCC capacitors

High Q capacitors - MS range

Ultra-low ESR capacitors

StackiCap™ capacitors

Non-magnetic capacitors

X8R High Temperature capacitors

Open Mode and Tandem capacitors

IECQ-CECC & AEC-Q200 ranges

S02A Space grade ranges

Safety Certified capacitors

250Vac Non Safety rated AC capacitors

115Vac 400Hz capable capacitors

High Dielectric Withstand Voltage ranges

E01 & E07 feedthrough chip capacitors

X2Y Integrated Passive Components

Radial Leaded capacitors









Introduction to Syfer Technology

First in the market with flexible polymer terminations

- the revolutionary FlexiCap™ capacitors - our capacitor range also includes: ProtectiCap™, high voltage capacitors, X8R high temperature types, High Q capacitors and other application specific types. Our renowned high voltage MLCC expertise has led to the development of an impressive range with working voltage capability up to 12kV. This includes surface mount Class 'X' and 'Y' approved Safety Certified capacitors, 0603 chips with working voltages up to 500V and 0805 types up to 2kV.

As part of the Dover Ceramic & Microwave Products group (CMP), we are able to offer unrivalled product quality with short lead-times, backed up by excellent sales and technical support. With a commitment to product innovation, new ranges are continually being developed.

Our experienced applications engineers are also available to provide custom solutions for specific applications. This catalogue details the standard ranges but we can provide items such as tight tolerance, low profile and non standard sizes on request. Flexibility is key, not only in design but in all aspects of customer service and support.

Our quality management systems meet international requirements, with approval to ISO 9001, environmental approval to ISO 14001 and Occupational Health and Safety approval to OHSAS 18001. Product approvals include, IECQ-CECC, UL, TÜV and qualification to AEC-Q200. SPC is used extensively, supported by Continuous Improvement Programmes, 6 Sigma projects and Lean Manufacturing initiatives.

Products

Syfer's excellence in ceramic materials technology, has enabled us to offer an unrivalled range of multilayer ceramic products including:

- Multilayer ceramic chip capacitors
- High voltage MLCCs
- ProtectiCap[™] capacitors
- FlexiCap[™] capacitors with flexible terminations
- StackiCap[™] capacitors
- Class 'X' and 'Y' SMD Safety Certified capacitors
- Radial leaded capacitors
- AEC-Q200 qualified capacitors
- IECQ CECC approved capacitors
- Capacitors for space applications
- High Q capacitors
- Non-magnetic capacitors
- 3 terminal EMI chips
- X2Y Integrated Passive Components

Benefits

- High quality and reliability
- World-leading high voltage expertise
- Suitable for the most demanding applications including: automotive, aerospace, military, space and medical
- Approvals to international specifications
- Continual product improvement and innovation
- Tight tolerances available
- Large case sizes, up to 8060
- Custom product capability
- Strong technical support
- Short lead-times
- Environmentally responsible

Suffix code controlled items such as Low profile, defined thickness and custom lead forms available by special request.

Other Syfer products

- Surface mount Pi filters
- Panel mount threaded filters
- Panel mount solder-in filters
- Custom filter assembly capability
- Varistor filters
- Discoidal capacitors
- Planar capacitor and planar varistor arrays
- EMI Power Filters
- Hermetically sealed EMI filters







Contents

Syfer - Innovative, World-Class Ceramic Capacitors

	General introduction	
	Definitions of Ultra-Stable and Stable	2
	Dielectric characteristics	3
	Capacitance, Impedance and E.S.R. vs Frequency	4
	Ageing, capacitance measurements and tight tolerance capacitors	5
	Production processes and reliability	6
	FlexiCap [™] overview	7
	Testing and termination types	8
	Documentation and compliance	9
	IECQ-CECC and AEC-Q200 periodic tests	10
	Handling notes	11
	Soldering information	12
	Chip dimensions	13
	Product Selector	14-15
	Ceramic Chip capacitors	
	Standard MLCC ranges - 10Vdc to 12kVdc - C0G/NP0 & X7R	16-18
	ProtectiCap™ capacitors	19
	TCC/VCC capacitors	20-21
	High Q capacitors - MS range	22-23
	Ultra-low ESR capacitors	24
	StackiCap™ capacitors	25
	Non-magnetic capacitors	26-27
	Non-magnetic Ribbon Leaded capacitors	28
5/3	Open Mode & Tandem capacitors	29
	IECQ-CECC range	30
ESP	AEC-Q200 range	31
	S02A Space grade range	32
C42-2	Safety Certified capacitors	33-35
delle	250Vac Non Safety rated AC capacitors	36
	115Vac 400Hz capacitors	37
	High Dielectric Withstand Voltage range	38
	X8R High Temperature capacitors	39
	Surface Mount EMI filters	
	E01 & E07 feedthrough chip capacitors	40-41
	X2Y Integrated Passive Components	42-43
	Packaging information - Ceramic chip capacitors	44-45
G	Radial Leaded capacitors	46-51
	Packaging information - Radial Leaded capacitors	52-53

MLCC standard range 10V to 12kVdc Contents

Notes: 1) Capacitance in F. 2) *These parts may require conformal coating post soldering. 3) T = Maximum thickness. 4) †Higher capacitance values available from the ProtectiCapTM range - see page 19. 5) StackiCapTM high capacitance versions are now available. Please refer to datasheet.

	10	V		16V		25	V	į	50/	′63V	10	00V	20 25		500	V	630	OV	1k	V	1.2	kV	1.5	kV	2k	ίV	2.5	kV	3k	V	4k	V	5k	V	6k	ίV	81	kV	10	kV	12	kV	
	COG/ NPO	X5R	COG/ NPO	X7R X5I	CO NF	G/ P0 X71	R X5F	COC NP	G/ 00 X	C7R X5R	COG/ NPO	X7R	COG/ NPO	X7R	COG/ NPO	X7R	COG/ NPO	X7R	COG/ NPO	X7R	COG/ NPO	X7R	COG/ NPO	X7R	COG/ NPO	X7R	COG/ NPO	X7R	COG/ NPO	X7R	C0G/ NP0	X7R	COG/ NPO	X7R	COG/ NPO	X7R	C0G/ NP0	X7R	COG/ NPO	X7R	COG/ NP0		
0603	0.47p - 3.9n	120n - 150n	0.47p - 2.7n	100p - 100n	n -	7p 100 - 2n 100		0.47 - 1.5		00p 56n 47n 68n	0.47p - 470p	- '	0.47p - 220p	100p - 10n	0.47p - 150p*	100p - 1.5n*	-	_	-	_	_	_	_	-	_	-	-	-	-	_	-	_	_	-	_	-	-	-	-	-	-	-	0603
0805	1.0p - 15n	390n - 680n	1.0p - 12n	100p 390 330n 470	n 1.0 - n 10			n 1.0 - n 5.6		00p 270n 20n 330n	1.0p - 2.2n		1.0p - 1n	100p - 56n	1.0p - 680p	100p - 15n	1.0p - 560p	100p - 12n	1.0p - 180p	100p - 10n	1.0p - 120p	_	1.0p - 82p	_	1.0p - 39p	_	_	-	_	_	_	_	_	_	_	-	_	-	_	-	_	-	0805
1206	1.0p - 47n	1.2µ - 1.5µ	1.0p - 33n	100p - 1.2µ 1.0µ	- ي	0p 100 - n 820	1.0	1.0 - 22i		00p 560n 70n 680n	1.0p - 8.2n	100p - 330n	1.0p - 3.3n	100p - 150n	1.0p - 2.2n	100p - 68n	1.0p - 1.5n	100p - 47n	1.0p - 1.0n	100p - 27n	1.0p - 680p	100p - 15n	1.0p - 330p	100p - 10n	1.0p - 220p	100p - 2.2n [†]	1.0p - 100p	-	1.0p - 68p	_	-	-	_	-	_	-	-	-	-	-	_	-	1206
1210	3.9p - 100n	1.8µ - 3.3µ	3.9p - 68n	100p 1.8µ 1.5µ 2.7µ	3.9 - u 56		-	3.9 - u 33i		00p 1.2μ Ι.0μ 1.5μ	3.9p - 18n		3.9p - 8.2n	100p - 330n	3.9p - 6.8n	100p - 150n	3.9p - 3.9n	100p - 100n	3.9p - 2.2n	100p - 47n	3.9p - 1.5n	100p - 18n	3.9p - 820p	100p - 12n	3.9p - 390p	100p - 4.7n [†]	3.9p - 220p	_	3.9p - 150p	_	-	_	_	_	_	-	-	-	-	-	_	-	1210
1808	4.7p - 100n	1.8µ - 2.7µ	4.7p - 68n	100p 1.8µ 1.5µ 2.2µ	-	7p 100	р 1.5µ	4.7 J -	p 10	00p 820n 80n 1.0µ	4.7p - 18n		4.7p - 8.2n	100p - 270n	4.7p - 5.6n	100p - 150n	4.7p - 3.9n	100p - 100n	4.7p - 2.2n	100p - 47n	4.7p - 1.5n	100p - 22n	4.7p - 1.0n	100p - 15n	4.7p - 470p	100p - 4.7n [†]	4.7p - 270p	100p - 1.5n [†]	4.7p - 180p	100p - 1.2n [†]	4.7p - 120p*	100p - 1.0n*†	4.7p - 68p*	100p - 680p*†	4.7p - 47p*	100p - 390p* ¹	_	_	-	_	_	-	1808
1812	10p - 220n	3.9µ - 10u	10p - 180n	150p 3.9µ 3.3µ 6.8µ	ı 10	p 150		10 ₁ -		50p 2.7µ 2.2µ 3.3µ	10p - 47n	-	10p - 22n	150p - 680n	10p - 15n	150p - 330n	10p - 10n	150p - 180n	10p - 6.8n	150p - 100n	10p - 4.7n	150p - 33n	10p - 2.7n	150p - 22n	10p - 1.5n	150p - 10n [†]	10p - 820p	150p - 3.3n [†]	10p - 560p	150p - 2.7n†	10p - 270p*	150p - 2.2n*†	10p - 180p*	150p - 1.2n*†	10p - 120p*	150p - 1.0n*†	_	_	-	-	-	-	1812 T=2.5mm
1812 =3.2mm	_		_		-		=	_		-	-	_	27n	- 1000n	18n -	- 470n	12n	- 330n	8.2n	- 180n	5.6n - 6.8n	_	3.3n	- 56n	1.8n	_	1.0n		680p	_	330p - 390p*	_	220p - 270p*	_	150p - 180p*	_	-	_	-	_	-	_	1812 T=3.2mm
1825 =2.5mm	10p - 470n	5.6µ - 15µ	10p - 330n	220p 5.6µ 4.7µ 12µ	10 - 220			10 ₁ - 150		20p 2.2µ I.8µ 6.8µ	10p - 68n	220p - 1.5µ	10p - 33n	220p - 1.0µ	10p -	220p - 560n	10p - 22n	220p - 180n	10p - 12n	220p - 120n	10p - 6.8n	220p - 68n	10p - 4.7n	220p - 47n	10p - 3.3n	220p - 10n	10p - 1.5n	220p - 6.8n	10p - 1.2n	220p - 3.9n	10p -	220p - 2.2n*	10p - 390p*	220p - 1.8n*	10p - 270p*	220p -	-	_	-	_	-	-	1825 T=2.5mm
1825 =3.2mm	_		_		-		_	-			_	_	39n - 47n	_	33n	_	27n	_	15n	_	8.2n - 10n	_	5.6n - 6.8n	_	3.9n	_	1.8n - 2.2n	_	1.5n	_	680p*	_	470p*	_	330p*		-	_	-	_	-	_	1825 T=3.2mm
2220 =2.5mm	10p - 470n	6.8µ - 18µ	10p - 330n	220p 6.8µ 5.6µ 12µ	1 10		-			20p 3.9µ 3.3µ 6.8µ	10p - 68n	-	10p - 33n	220p - 1.0µ	10p - 22n	220p - 560n	10p - 18n	220p - 330n	10p - 15n	220p - 120n	10p - 10n	220p - 82n	10p - 5.6n	220p - 47n	10p - 3.3n	220p - 27n [†]	10p - 1.8n	220p - 8.2n [†]	10p - 1.5n	220p - 6.8n [†]	10p - 680p*	220p - 4.70*†	10p - 470p*	220p - 3.9n*†	10p - 330p*	220p -	_	_	_	_	_	_	2220 T=2.5mm
2220 =4.2mm	—	тоµ —	—	— — —	_		н Тор	-		— —	— Ooli		39n -		27n -	-	22n -		18n -	-	12n -	-	6.8n -	-	3.9n -	-	2.2n -		1.8n -	-	820p	4./II	560p	J.911"	390p	_	_	_	_	_	_	_	2220 T=4.2mm
ZZZ3		8.2µ	10p -	330p 8.2µ	10	-	lp 6.8 ₁	يا 10 -		30p 3.9µ	10p	330p -	56n 10p	330p	39n 10p	330p -	33n 10p	330p	22n 10p	470n 330p	15n 10p	330p	10n 10p	330p	5.6n 10p	330p	3.3n 10p -	330p	2.2n 10p	330p	1.2n* 10p	330p	820p*	330p	560p*	330p -	_	_	_	_	_	_	2225 T=2.5mm
2225 =4.0mm	560n —	22µ —	470n —	6.8µ 15µ — —	330	On 5.6	μ 12μ —	220	On 3	— — — — — — — — — — — — — — — — —	82n —	2.7µ —	47n 56n -	1.5µ —	39n -	820n —	27n -	390n —	18n 22n -	150n —	12n 15n -	100n —	6.8n 8.2n	68n —	4.7n 5.6n	33n —	2.2n 2.7n -	12n —	1.8n 2.2n -	8.2n —	820p* 1.0n -	5.6n* —	680p	4.7n* —	390p* 470p -		_	_	_	_	 _	_	2225 T=4.0mm
3640	_							10		70p	10p		68n 10p -	470p -	47n 10p -	470p -	39n 10p	470p -	27n 10p -	470p -	22n 10p	470p -	12n 10p -	470p -	6.8n 10p -	470p -	3.9n 10p -	470p -	2.7n 10p -	470p -	1.5n* 10p -	470p -	1.0n* 10p -	470p -	680p* 10p	470p -	-	470p -	-	470p -	10p -	-	3640
=2.5mm 3640	_			5/5	YF	ER	7	330		10µ	270n	5.6µ —	120n 150n -	3.3µ —	82n 100n -	1.0µ	68n 82n	680n —	47n 56n	180n —	33n 39n	150n —	22n 27n -	100n —	10n 12n -	47n —	6.8n 8.2n -	33n —	4.7n 5.6n -	22n —	2.2n -	6.8n —	1.5n 1.8n	5.6n	1.0n 1.2n	_	150p —	1.5n* —	100p	1.0n* —	68p —	820p* —	T=2.5mm
5550			CM	P		WIR COMPAN		390		1.0n	390p	1.0n	180n 390p	1.0n -	120n 390p	1.0n -	100n 390p -	1.0n -	82n 390p -	1.0n -	56n 390p	1.0n -	39n 390p	1.0n -	18n 390p	1.0n -	12n 390p -	1.0n -	8.2n 390p -	1.0n -	3.3n 390p	1.0n -	2.2n 390p	1.0n -	1.5n 390p		27p	1.0n	100	1.0n -	27p -	1.0n	T=4.0mm
5550 =4.0mm		2	211 c	402, 050 ase sizes a ciality rai	are a	vailabl		680		15µ	470n	10µ	270n 330n	5.6µ	180n 220n	1.8µ	120n 150n -	1.2µ	82n 100n	390n —	68n 82n	220n —	39n 47n	150n	22n 27n	82n —	12n 15n -	68n	10n 12n	47n —	4.7n 5.6n	15n	2.7n 3.3n	10n	1.8n 2.2n		330p	4.7n*	180p	2.2n* —	120p	1.2n*	T=2.5mm
=4.0mm 3060		Р	lease	refer to the s of this o	ne re	levant		680		2.2n	680p	2.2n	680p	2.2n	270n 680p	 2.2n	180n 680p	2.2n	150n 680p	2.2n	100n 680p	 2.2n	68n 680p	2.2n	39n 680p	2.2n	22n 680p	2.2n	18n 680p	2.2n	6.8n 680p	2.2n	4.7n 680p	2.2n	3.3n 680p	1.8n	47p	1.8n	47p	1.8n	 47р	1.8n	T=4.0mm
3060			nore d					1.0)μ 2	22µ	680n	- 15µ	390n 470n	10µ	330n	3.3µ	270n	2.2µ	150n 180n	1.0µ	100n 120n	470n	68n 82n	330n	- 39n 47n	150n	22n 27n	100n	15n 18n	82n	8.2n 10n	33n	5.6n 6.8n	22n	3.9n 4.7n	15n	680p	- 6.8n*	470p	4.7n*	220p	2.2n*	T=2.5mm
=4.0mm													560n	0/	- 470n		- 390n		- 270n		- 180n		- 120n		- 68n		- 39n		- 27n		- 15n		10n		- 6.8n							_	T=4.0mm
	10	V		16V		25	V	!	50/	63V	10	V	250		500	V	630	0V	1k	V	1.2	kV	1.5	kV	2k	(V	2.5	kV	3k	V	4k	V	5k	V	6k	ΚV	81	kV	10	kV	12	kV	

Syfer - Innovative, World-Class Ceramic Capacitors

	General introduction	
	Definitions of Ultra-Stable and Stable	
	Dielectric characteristics	;
	Capacitance, Impedance and E.S.R. vs Frequency	
	Ageing, capacitance measurements and tight tolerance capacitors	Į.
	Production processes and reliability	
	FlexiCap™ overview	
	Testing and termination types	
	Documentation and compliance	
	IECQ-CECC and AEC-Q200 periodic tests	10
	Handling notes	1
	Soldering information	1:
	Chip dimensions	13
	Product Selector	14-1
	Ceramic Chip capacitors	
	Standard MLCC ranges - 10Vdc to 12kVdc - C0G/NP0 & X7R	16-18
	ProtectiCap™ capacitors	19
	TCC/VCC capacitors	20-2
	High Q capacitors - MS range	22-2
	Ultra-low ESR capacitors	2
	StackiCap™ capacitors	2!
	Non-magnetic capacitors	26-2
	Non-magnetic Ribbon Leaded capacitors	28
212	Open Mode & Tandem capacitors	29
	IECQ-CECC range	30
CS8	AEC-Q200 range	3
	S02A Space grade range	3
dr. Cl	Safety Certified capacitors	33-3
	250Vac Non Safety rated AC capacitors	3
	115Vac 400Hz capacitors	3
	High Dielectric Withstand Voltage range	38
	X8R High Temperature capacitors	39
	Surface Mount EMI filters	
	E01 & E07 feedthrough chip capacitors	40-4
	X2Y Integrated Passive Components	42-43
	Packaging information - Ceramic chip capacitors	44-4
G	Radial Leaded capacitors	46-5
	Packaging information - Radial Leaded capacitors	52-5

Multilayer Ceramic Capacitors are generally divided into classes which are defined by the capacitance temperature characteristics over specified temperature ranges. These are designated by alpha numeric codes. Code definitions are summarised below and are also available in the relevant national and international specifications.

COG/NPO - Ultra Stable Class 1 Ceramic (EIA Class 1)

Spec.	Classification	Temperature range °C	Maximum capacitance change @ rated DC volts	Syfer dielectric code
CECC	1B/CG	-55 +125	0 ± 30ppm/°C	С
EIA	COG/NPO	-55 +125	0 ± 30ppm/°C	С
MIL	CG (BP)	-55 +125	0 ± 30ppm/°C	С

Capacitors within this class have a dielectric constant range from 10 to 100. They are used in applications which require ultra stable dielectric characteristics with negligible dependence of capacitance and dissipation factor with time, voltage and frequency. They exhibit the following characteristics:-

- a) Time does not significantly affect capacitance and dissipation factor (Tan δ) no ageing.
- b) Capacitance and dissipation factor are not affected by voltage.
- c) Linear temperature coefficient.

X8R, X7R and X5R - Stable Class II Ceramic (EIA Class II)

Spec.	Classification	Temperature	Maximum capaci over temper	Syfer dielectric	
Орсс.	Cidosificación	range °C	No DC volt applied	Rated DC Volt	code
	2C1	-55 +125	±20	+20 -30	R
CECC	2R1	-55 +125	±15		X
	2X1	-55 +125	±15	+15 -25	В
	X8R	-55 +150	±15		N
EIA	X7R	-55 +125	±15		X
	X5R	-55 +85	±15		Р
N/III	ВХ	-55 +125	±15	+15 -25	В
MIL	BZ	-55 +125	±20	+20 -30	R

Capacitors of this type have a dielectric constant range of 1000-4000, and also have a non-linear temperature characteristic which exhibits a dielectric constant variation of less than $\pm 15\%$ (2R1) from its room temperature value, over the specified temperature range. Generally used for by-passing (decoupling), coupling, filtering, frequency discrimination, DC blocking and voltage transient suppression


with greater volumetric efficiency than Class I units, whilst maintaining stability within defined limits.


Capacitance and dissipation factor are affected by:-Time (Ageing)

Voltage (AC or DC)

Frequency

Typical dielectric temperature characteristics






Temperature (°C)

X7R capacitance vs

Power ratings

COG/NPO and X7R



Technical Summary

Technical Summary


	C	OG/NP	0	X5R		X7R		X8R
Dielectric characteristics	l	Ultra stable	=	Stable		Stable		Stable
IECQ- CECC	1B/CG	-	-	-	2C1	2R1	2X1	-
EIA	-	COG/ NPO	-	X5R	-	X7R	-	X8R
MIL	-	-	CG (BP)	-	BZ	-	ВХ	-
Rated temperature range	-55	°C to +12	5°C	-55°C to +85°C	-55	o°C to +12	5°C	-55°C to +150°C
Maximum capacitance change over temperature range No DC voltage applied	0 :	± 30 ppm/	°C	± 15%	± 20%	± 15%	± 15%	± 15%
Rated DC voltage applied				-	+20 -30%	-	+15 -25%	-
Syfer dielectric ordering code		С		Р	R	х	В	N
Tangent of loss angle (tan δ)		i ≤ 0.0015 i = 0.0015	(<u>15</u> + 0.7) Cr	≤ 0.025		≤ 0.025		≤ 0.025
Insulation resistance (Ri) Time constant (Ri x Cr) (whichever is the least)	100G Ω or 1000s			100G Ω or 1000s	100G Ω or 1000s			100G Ω or 1000s
Capacitance tolerance	Cr <4.7pF Cr <10pF Cr ≥10pF	± 0.0 ± 0.0 ± 0.0 ± 0.0 ± 0.0 ± 19 ± 29 ± 59	6 (G)	±5% (J) ±10% (K) ±20% (M)	± 1	% (J) 0% (K) 0% (M)		± 5% (J) ± 10% (K) ± 20% (M)
Dielectric strength				Voltage applied Charging current limit			um.	
≤200V >200V to <500V 500V to ≤1000V 500V to <1000V >1kV to ≤1200V >1200V ≥1000V	>200V to <500V 500V to ≤1000V 500V to <1000V >1.5 times -1.25 times -1.200V 1.25 times		2.5 times	2.5 times	tage + 250		2.5 times	
Climatic category (IEC)								
Chip	55/125/56			55/85/56		55/125/56		55/150/56
Dipped	55/125/21			-		55/125/21		-
Discoidal	55/125/56			-	55/125/56			-
Ageing characteristic Zero (Typical)		<2% per time decade	<2% per time decade		ecade	<2% per time decade		

The table above highlights the difference in coding for IECQ-CECC, EIA and MIL standards when defining the temperature coefficient and the voltage coefficient.

Approvals				
Chip	QC-32100	-	QC-32100	-


Impedance vs Frequency - chips

Ultra Stable COG/NPO dielectric




ESR vs Frequency - chips


Ultra Stable COG/NPO dielectric



Stable X7R dielectric




Stable X7R dielectric



Impedance vs Frequency - 10nF chips

Stable X7R dielectric



Ageing

Capacitor ageing is a term used to describe the negative, logarithmic capacitance change which takes place in ceramic capacitors with time. The crystalline structure for barium titanate based ceramics changes on passing through its Curie temperature (known as the Curie Point) at about 125°C. This domain structure relaxes with time and in doing so, the dielectric constant reduces logarithmically; this is known as the ageing mechanism of the dielectric constant. The more stable dielectrics have the lowest ageing rates.

The ageing process is reversible and repeatable. Whenever the capacitor is heated to a temperature above the Curie Point the ageing process starts again from zero.

The ageing constant, or ageing rate, is defined as the percentage loss of capacitance due to the ageing process of the dielectric which occurs during a decade of time (a tenfold increase in age) and is expressed as percent per logarithmic decade of hours. As the law of decrease of capacitance is logarithmic, this means that in a capacitor with an ageing rate of 1% per decade of time, the capacitance will decrease at a rate of:

- a) 1% between 1 and 10 hours
- b) An additional 1% between the following 10 and 100 hours
- An additional 1% between the following 100 and 1000 hours
- d) An additional 1% between the following 1000 and 10000 hours etc
- The ageing rate continues in this manner throughout the capacitor's life.

Typical values of the ageing constant for our Multilayer Ceramic Capacitors are:

Dielectric class	Typical values
Ultra Stable COG/NP0	Negligible capacitance loss through ageing
Stable X7R	<2 % per decade of time


Capacitance measurements

Because of ageing it is necessary to specify an age for reference measurements at which the capacitance shall be within the prescribed tolerance. This is fixed at 1000 hours, since for practical purposes there is not much further loss of capacitance after this time.

All capacitors shipped are within their specified tolerance at the standard reference age of 1000 hours after having cooled through their Curie temperature.

The ageing curve for any ceramic dielectric is a straight line when plotted on semi-log paper.

Capacitance vs time (Ageing X7R @ 1% per decade)




Tight tolerance


One of the advantages of Syfer's unique 'wet process' of manufacture is the ability to offer capacitors with exceptionally tight capacitance tolerances.

The accuracy of the printing screens used in the fully automated, computer controlled manufacturing process allows for tolerance as close as +/-1% on COG/NPO parts greater than or equal to 10pF. For capacitance values below <4.7pF, tolerances can be as tight as +/-0.05pF.

Production process flowchart




Syfer reliability grades



Notes:

- Space grade tested in accordance with ESCC 3009. Refer to Syfer specification S02A 0100.
- MIL Grade. Released in accordance with US standards available on request.
- (3) IECQ-CECC. The International Electrotechnical Commission (IEC) Quality Assessment System for Electronic Components. This is an internationally recognised product quality certification which provides customers with assurance that the product supplied meets high quality standards.
 - View Syfer's IECQ-CECC approvals at http://www.iecq.org or at www.syfer.com
- (4) AEC-Q200. Automotive Electronics Council Stress Test Qualification For Passive Components. Refer to Syfer application note reference AN0009.

Syfer reliability surface mount product groups



Notes

- (1) "Tandem" construction capacitors, ie internally having the equivalent of 2 series capacitors. If one of these should fail short-circuit, there is still capacitance end to end and the chip will still function as a capacitor, although capacitance maybe affected. Refer to application note AN0021. Also available qualified to AEC-Q200.
- (2) "Open Mode" capacitors with FlexiCap™ termination also reduce the possibility of a short circuit by utilising inset electrode margins. Refer to application note AN0022. Also available qualified to AEC-Q200.
- (3) Multilayer capacitors with Syfer FlexiCap™ termination. By using FlexiCap™ termination, there is a reduced possibility of the mechanical cracking occurring.
- (4) "Standard" capacitors includes MLCCs with tin finish over nickel, but no FlexiCap™.

FlexiCap™ termination

Technical Summary

MLCCs are widely used in electronic circuit design for a multitude of applications. Their small package size, technical performance and suitability for automated assembly makes them the component of choice for the specifier.

However, despite the technical benefits, ceramic components are brittle and need careful handling on the production floor. In some circumstances they may be prone to mechanical stress damage if not used in an appropriate manner. Board flexing, depanelisation, mounting through hole components, poor storage and automatic testing may all result in cracking.

Careful process control is important at all stages of circuit board assembly and transportation - from component placement to test and packaging. Any significant board flexing may result in stress fractures in ceramic devices that may not always be evident during the board assembly process. Sometimes it may be the end customer who finds out - when equipment fails!

Syfer has the solution - FlexiCap™


FlexiCap™ has been developed as a result of listening to customers' experiences of stress damage to MLCCs from many manufacturers, often caused by variations in production processes.

Our answer is a proprietary flexible epoxy polymer termination material, that is applied to the device under the usual nickel barrier finish. FlexiCap™ will accommodate a greater degree of board bending than conventional capacitors.

Syfer FlexiCap™ termination

Ranges are available with FlexiCap™ termination material offering increased reliability and superior mechanical performance (board flex and temperature cycling) when compared with standard termination materials. Refer to Syfer application note reference AN0001. FlexiCap™ capacitors enable the board to be bent almost twice as much before mechanical cracking occurs. Refer to application note AN0002.

FlexiCap™ is also suitable for Space applications having passed thermal vacuum outgassing tests. Refer to Syfer application note reference AN0026.



FlexiCap™ MLCC cross section

FlexiCap™ benefits

With traditional termination materials and assembly, the chain of materials from bare PCB to soldered termination, provides no flexibility. In circumstances where excessive stress is applied - the weakest link fails. This means the ceramic itself, which may fail short circuit.

The benefit to the user is to facilitate a wider process window - giving a greater safety margin and substantially reducing the typical root causes of mechanical stress cracking.

FlexiCap™ may be soldered using your traditional wave or reflow solder techniques including lead free and needs no adjustment to equipment or current processes.

Syfer has delivered millions of FlexiCap™ components and during that time has collected substantial test and reliability data, working in partnership with customers world wide, to eliminate mechanical cracking.

An additional benefit of FlexiCap $^{\text{TM}}$ is that MLCCs can withstand temperature cycling -55°C to 125°C in excess of 1,000 times without cracking.

FlexiCap[™] termination has no adverse effect on any electrical parameters, nor affects the operation of the MLCC in any way.



● Picture taken at 1,000x magnification using a SEM to demonstrate the fibrous nature of the FlexiCap™ termination that absorbs increased levels of mechanical stress.

Available on the following ranges:

- All High Reliability ranges
- Standard and High Voltage chips
- Safety Certified capacitor chips
- Non-magnetic capacitors
- 3 terminal EMI chips
- X2Y Integrated Passive Components
- X8R High Temperature capacitors

Summary of PCB bend test results

The bend tests conducted on X7R have proven that the FlexiCap™ termination withstands a greater level of mechanical stress before mechanical cracking occurs.

The AEC-Q200 test for X7R requires a bend level of 2mm minimum and a cap change of less than 10%.

Product X7R	Typical bend performance under AEC-Q200 test conditions
Standard termination	2mm to 3mm
FlexiCap™	Typically 8mm to 10mm

Application notes

FlexiCapTM may be handled, stored and transported in the same manner as standard terminated capacitors. The requirements for mounting and soldering FlexiCapTM are the same as for standard SMD capacitors.

For customers currently using standard terminated capacitors there should be no requirement to change the assembly process when converting to $FlexiCap^{TM}$.

Based upon board bend tests in accordance with IEC 60384-1 the amount of board bending required to mechanically crack a FlexiCap™ terminated capacitor is significantly increased compared with standard terminated capacitors.

It must be stressed however, that capacitor users must not assume that the use of FlexiCap $^{\text{TM}}$ terminated capacitors will totally eliminate mechanical cracking. Good process controls are still required for this objective to be achieved.



Tests conducted during batch manufacture		Syfer reliability S	M product group	
manuracture	Standard SM capacitors	IECQ-CECC / MIL grade	AEC-Q200	S (Space grade) High Rel S02A
Solderability	•	•	•	•
Resistance to soldering heat	•	•	•	•
Plating thickness verification (if plated)	•	•	•	•
DPA (Destructive Physical Analysis)	•	•	•	•
Voltage proof test (DWV / Flash)	•	•	•	•
Insulation resistance	•	•	•	•
Capacitance test	•	•	•	•
Dissipation factor test	•	•	•	•
100% visual inspection	0	0	•	•
100% burn-in. (2xRV @125°C for 168 hours)	0	0	0	•
Load sample test @ 125°C	O	0	O	LAT1 & LAT2 (1000 hours)
Humidity sample test. 85°C/85%RH	0	0	0	240 hours
Hot IR sample test	0	0	0	0
Axial pull sample test (MIL-STD-123)	0	0	0	0
Breakdown voltage sample test	О	0	0	0
Deflection (bend) sample test	0	0	0	0
SAM (Scanning Acoustic Microscopy)	0	0	0	0
LAT1 (4 x adhesion, 8 x rapid temp change + LAT2 and LAT3)	-	-	-	0
LAT2 (20 x 1000 hour life test + LAT3)	-	-	-	0
LAT3 (6 x TC and 4 x solderability)	-	-	-	0

Test conducted as standard.

Optional test. Please discuss with the sales office.

Termination types available	Syfer reliability SM product group							
	Standard SM capacitors	IECQ-CECC / MIL grade	AEC-Q200	S (space grade) High Rel S02A				
F: Silver palladium	•	•	-	•				
J: Silver base with nickel barrier (100% matte tin plating)	•	•	COG/NP0 dielectric only	0				
A: Silver base with nickel barrier (tin/lead plating with min 10% lead)	•	•	-	•				
Y: FlexiCap™ with nickel barrier (100% matte tin plating)	•	•	•	0				
H: FlexiCap [™] with nickel barrier (tin/lead plating with min 10% lead)	•	•	-	0				
2: Silver base with Non-magnetic Cu Barrier (100% matte tin plating)	(1)	-	-	-				
3: FlexiCap [™] with Non-magnetic Cu Barrier (100% matte tin plating)	(2)	-	-	-				

Notes

- (1) Available on COG/NPO and High Q only.
- (2) Available on all dielectrics.
- Termination available.
- O Termination available but generally not requested for space grade components.

Please discuss with the sales office.

Release documentation	Syfer reliability SM product group							
	Standard SM capacitors	IECQ-CECC	AEC-Q200 MIL grade	S (Space grade) High Rel S02A				
Certificate of conformance	•	-	•	•				
IECQ-CECC Release certificate of conformity	-	•	-	-				
Batch electrical test report	0	О	0	Included in data pack				
S (space grade) data documentation package	-	-	-	•				

- Release documentation supplied as standard.
- Original documentation.

Periodic tests conducted and reliability data availability

Standard Surface Mount capacitors

Components are randomly selected on a sample basis and the following routine tests are conducted:

- Load Test. 1,000 hours @125°C (150°C for X8R). Applied voltage depends on components tested.
- Humidity Test. 168 hours @ 85°C/85%RH.
- Board Deflection (bend test).


Test results are available on request.

Conversion factors

From	То	Operation
FITS	MTBF (hours)	10 ⁹ ÷ FITS
FITS	MTBF (years)	10 ⁹ ÷ (FITS x 8760)

FITS = Failures in 10⁹ hours. MTBF = Mean time between failures.

Example of FIT (Failure In Time) data available:



Component type: 0805 (C0G/NP0 and X7R).

Testing location: Syfer reliability test department.

Results based on: 16,622,000 component test hours.

REACH (Registration, Evaluation, Authorisation and restriction of Chemicals) statement

The main purpose of REACH is to improve the protection of human health and the environment from the risks arising from the use of chemicals.

Syfer Technology Ltd maintains both ISO14001, Environmental Management System and OHSAS 18001 Health and Safety Management System approvals that require and ensure compliance with corresponding legislation such as REACH. For further information, please contact the sales office at sales@syfer.co.uk

RoHS compliance

Syfer routinely monitors world wide material restrictions (e.g. EU / China and Korea RoHS mandates) and is actively involved in shaping future legislation.

All standard COG/NPO, X7R, X5R and High Q Syfer MLCC products are compliant with the EU RoHS directive (see below

for special exceptions) and those with plated terminations are suitable for soldering using common lead free solder alloys (refer to 'Soldering Information' for more details on soldering limitations). Compliance with the EU RoHS directive automatically signifies compliance with some other legislation (e.g. Korea RoHS). Please refer to the sales office for details of compliance with other materials legislation.

Breakdown of material content, SGS analysis reports and tin whisker test results are available on request.

Most Syfer MLCC components are available with non RoHS compliant tin lead (SnPb) solderable termination finish for exempt applications and where pure tin is not acceptable. Other tin free termination finishes may also be available – please refer to the sales office for further details.

Radial components have tin plated leads as standard but tin/ lead is available as a special option. Please refer to the radial section of the catalogue for further details.

X8R ranges <250Vdc are not RoHS 2011/65/EU compliant. Check the website, www.syfer.com for latest RoHS update.

Export controls and dual-use regulations

Certain Syfer catalogue components are defined as 'dual-use' items under international export controls - those that can be used for civil or military purposes which meet certain specified technical standards.

The defining criteria for a dual-use component with respect to Syfer products is one with a voltage rating of >750V and a capacitance value >250nF and a series inductance <10nH.

Components defined as 'dual-use' under the above criteria automatically require a licence for export outside the EU, and

may require a licence for export within the EU.

The application for a licence is routine, but customers for these products will be asked to supply further information. Please refer to the sales office if you require any further information on export restrictions.

Other special components may additionally need to comply with export regulations.

Periodic tests conducted for IECQ-CECC and AEC-Q200

Test	Test Termination			Sample acceptance			
ref	Test	type	Additional requirements	P	N N	C	Reference
P1	High temperature exposure (storage)	All types	Un-powered. 1,000 hours @ T=150°C. Measurement at 24 ± 2 hours after test conclusion	12	77	0	MIL-STD-202 Method 108
P2	Temperature cycling	COG/NP0: All types X7R: Y and H only	1,000 cycles -55°C to +125°C Measurement at 24 \pm 2 hours after test conclusion	12	77	0	JESD22 Method JA-104
Р3	Moisture resistance	All types	T = 24 hours/cycle. Note: Steps 7a and 7b not required. Un-powered. Measurement at 24 \pm 2 hours after test conclusion	12	77	0	MIL-STD-202 Method 106
P4	Biased humidity	All types	1,000 hours 85°C/85%RH. Rated voltage or 50V whichever is the least and 1.5V. Measurement at 24 ± 2 hours after test conclusion	12	77	0	MIL-STD-202 Method 103
P5	Operational life	All types	Condition D steady state TA=125°C at full rated. Measurement at 24 \pm 2 hours after test conclusion	12	77	0	MIL-STD-202 Method 108
P6	Resistance to solvents	All types	Note: Add aqueous wash chemical. Do not use banned solvents	12	5	0	MIL-STD-202 Method 215
P7	Mechanical shock	COG/NP0: All types X7R: Y and H only	Figure 1 of Method 213. Condition F	12	30	0	MIL-STD-202 Method 213
P8	Vibration	COG/NP0: All types X7R: Y and H only	5g's for 20 minutes, 12 cycles each of 3 orientations. Note: Use 8" x 5" PCB 0.031" thick 7 secure points on one long side and 2 secure points at corners of opposite sides. Parts mounted within 2" from any secure point. Test from 10-2,000Hz	12	30	0	MIL-STD-202 Method 204
P9	Resistance to soldering heat	All types	Condition B, no pre-heat of samples: Single wave solder - Procedure 2	3	12	0	MIL-STD-202 Method 210
P10	Thermal shock	COG/NPO: All types X7R: Y and H only	-55°C/+125°C. Number of cycles 300. Maximum transfer time - 20 seconds, dwell time - 15 minutes. Air-Air	12	30	0	MIL-STD-202 Method 107
P11	Adhesion, rapid temp change and climatic sequence	X7R: A, F and J only	5N force applied for 10s, -55°C/ +125°C for 5 cycles, damp heat cycles	12	27	0	BS EN132100 Clause 4.8, 4.12 and 4.13
P12	Board flex	COG/NPO: All types X7R: Y and H only	3mm deflection Class I 2mm deflection Class II	12	30	0	AEC-Q200-005
P13		X7R: A, F and J only	1mm deflection.	12	12	0	BS EN132100 Clause 4.9
P14	Terminal strength	All types	Force of 1.8kg for 60 seconds	12	30	0	AEC-Q200-006
P15	Beam load test	All types		12	30	0	AEC-Q200-003
P16	Damp heat steady state	All types	56 days, 40°C / 93% RH 15x no volts, 15x 5Vdc, 15x rated voltage or 50V whichever is the least.	12	45	0	BS EN132100 Clause 4.14

Test results are available on request.

P = Period in months.

N = Sample size.

10

C = Acceptance criteria.

Detailed application notes intended to guide and assist our customers in using multilayer ceramic capacitors in surface mount technology are available on the Syfer website www.syfer.com

Technical Summary

The information concentrates on the handling, mounting, connection, cleaning, test and re-work requirements particular to MLC's for SMD technology, to ensure a suitable match between component capability and user expectation. Some extracts are given below.

Handling

Ceramics are dense, hard, brittle and abrasive materials. They are liable to suffer mechanical damage, in the form of chips or cracks, if improperly handled.

Terminations may be abraded onto chip surfaces if loose chips are tumbled in bulk. Metallic tracks may be left on the chip surfaces which might pose a reliability hazard.

Components should never be handled with fingers; perspiration and skin oils can inhibit solderability and will aggravate cleaning.

Chip capacitors should never be handled with metallic instruments. Metal tweezers should never be used as these can chip the product and may leave abraded metal tracks on the product surface. Plastic or plastic coated metal types are readily available and recommended - these should be used with an absolute minimum of applied pressure.

Counting or visual inspection of chip capacitors is best performed on a clean glass or hard plastic surface.

If chips are dropped or subjected to rough handling, they should be visually inspected before use. Electrical inspection may also reveal gross damage via a change in capacitance, an increase in dissipation factor or a decrease either in insulation resistance or electrical strength.

Transportation

Where possible, any transportation should be carried out with the product in its unopened original packaging. If already opened, any environmental control agents supplied should be returned to packaging and the packaging re-sealed.

Avoid paper and card as a primary means of handling, packing, transportation and storage of loose components. Many grades have a sulphur content which will adversely affect termination solderability.

Loose chips should always be packed with sulphur-free wadding to prevent impact or abrasion damage during transportation.

Storage

Incorrect storage of components can lead to problems for the user. Rapid tarnishing of the terminations, with an associated degradation of solderability, will occur if the product comes into contact with industrial gases such as sulphur dioxide and chlorine. Storage in free air, particularly moist or polluted air, can result in termination oxidation.

Packaging should not be opened until the MLC's are required for use. If opened, the pack should be re-sealed as soon as is practicable. Alternatively, the contents could be kept in a sealed container with an environmental control agent.

Long term storage conditions, ideally, should be temperature controlled between -5 and +40°C and humidity controlled between 40 and 60% R.H.

Taped product should be stored out of direct sunlight, which might promote deterioration in tape or adhesive performance.

Product, stored under the conditions recommended above, in its "as received" packaging, has a minimum shelf life of 2 years.

Mechanical considerations for mounted ceramic chip capacitors

Due to their brittle nature, ceramic chip capacitors are more prone to excesses of mechanical stress than other components used in surface mounting.

One of the most common causes of failure is directly attributable to bending the printed circuit board after solder attachment. The excessive or sudden movement of the flexible circuit board stresses the inflexible ceramic block causing a crack to appear at the weakest point, usually the ceramic/termination interface. The crack may initially be quite small and not penetrate into the inner electrodes; however, subsequent handling and rapid changes in temperature may cause the crack to enlarge.

This mode of failure is often invisible to normal inspection techniques as the resultant cracks usually lie under the capacitor terminations but if left, can lead to catastrophic failure. More importantly, mechanical cracks, unless they are severe may not be detected by normal electrical testing of the completed circuit, failure only occurring at some later stage after moisture ingression.

The degree of mechanical stress generated on the printed circuit board is dependent upon several factors including the board material and thickness; the amount of solder and land pattern. The amount of solder applied is important, as an excessive amount reduces the chip's resistance to cracking.

It is Syfer's experience that more than 90% are due to board depanelisation, a process where two or more circuit boards are separated after soldering is complete. Other manufacturing stages that should be reviewed include:

- Attaching rigid components such as connectors, relays, display panels, heat sinks etc.
- Fitting conventional leaded components. Special care must be exercised when rigid terminals, as found on large can electrolytic capacitors, are inserted.
- 3) Storage of boards in such a manner which allows warping.
- 4) Automatic test equipment, particularly the type employing "bed of nails" and support pillars.
- 5) Positioning the circuit board in its enclosure especially where this is a "snap-fit".

Syfer were the first MLCC manufacturer to launch a flexible termination to significantly reduce the instances of mechanical cracking. FlexiCap™ termination introduces a certain amount of give into the termination layer absorbing damaging stress. Unlike similar systems, FlexiCap™ does not tear under tension, but absorbs the stress, so maintaining the characteristics of the MLCC.

SM Pad Design

Syfer conventional 2-terminal chip capacitors can generally be mounted using pad designs in accordance with IPC-7351, Generic Requirements for Surface Mount Design and Land Pattern Standards, but there are some other factors that have been shown to reduce mechanical stress, such as reducing the pad width to less than the chip width. In addition, the position of the chip on the board should also be considered.

3-Terminal components are not specifically covered by IPC-7351, but recommended pad dimensions are included in the Syfer catalogue / website for these components.

Soldering information Technical Summary

Soldering information

Syfer MLCCs are compatible with all recognised soldering/ mounting methods for chip capacitors. A detailed application note is available on-line at www.syfer.com

Reflow soldering surface mount chip capacitors

Syfer recommend reflow soldering as the preferred method for mounting MLCCs. Syfer MLCCs can be reflow soldered using a reflow profile generally as defined in IPC / JEDEC J-STD-020. Sn plated termination chip capacitors are compatible with both conventional and lead free soldering, with peak temperatures of 260°C to 270°C acceptable.

The heating ramp rate should be such that components see a temperature rise of 1.5°C to 4°C per seconds to maintain temperature uniformity through the MLCC.

The time for which the solder is molten should be maintained at a minimum, so as to prevent solder leaching. Extended times above 230°C can cause problems with oxidation of Sn plating. Use of inert atmosphere can help if this problem is encountered. PdAg terminations can be particularly susceptible to leaching with lead free, tin rich solders and trials are recommended for this combination.

Cooling to ambient temperature should be allowed to occur naturally, particularly if larger chip sizes are being soldered. Natural cooling allows a gradual relaxation of thermal mismatch stresses in the solder joints. Forced cooling should be avoided as this can induce thermal breakage.

Wave soldering Chip and Radial Leaded capacitors

Wave soldering is generally acceptable, but the thermal stresses caused by the wave have been shown to lead to potential problems with larger or thicker chips. Particular care should be taken when soldering SM chips larger than size 1210 and with a thickness greater than 1.0mm for this reason.

0402 size components are not suitable for wave soldering. 0402 size components can also be susceptible to termination leaching and reflow soldering is recommended for this size MLCC.

Maximum permissible wave temperature is 270°C for SM chips and 260°C for Radial Leaded capacitors.

The total immersion time in the solder should be kept to a minimum. It is strongly recommended that Sn/Ni plated terminations are specified for wave soldering applications. PdAg termination is particularly susceptible to leaching when subjected to lead free wave soldering and is not generally recommended for this application.

Total immersion exposure time for Sn/Ni terminations is 30s at a wave temperature of 260°C. Note that for multiple soldering operations, including the rework, the soldering time is cumulative.

The pre-heat ramp should be such that the components see a temperature rise of 1.5°C to 4°C per second as for reflow soldering. This is to maintain temperature uniformity through the MLCC and prevent the formation of thermal gradients within the ceramic. The preheat temperature should be within 120°C maximum (100°C preferred) of the maximum solder temperature to minimise thermal shock.

Cooling to ambient temperature should be allowed to occur naturally, particularly if larger chip sizes are being soldered. Natural cooling allows a gradual relaxation of thermal mismatch stresses in the solder joints. Forced cooling should be avoided as this can induce thermal breakage.

12

Rework of Chip capacitors

Syfer recommend hot air/ gas as the preferred method for applying heat for rework. Apply even heat surrounding the component to minimise internal thermal gradients. Soldering irons or other techniques that apply direct heat to the chip or surrounding area, should not be used as these can result in micro cracks being generated.

Minimise the rework heat duration and allow components to cool naturally after soldering.

Hand soldering Radial Leaded capacitors

Radial capacitors can be hand soldered into boards using soldering irons, provided care is taken not to touch the body of the capacitor with the iron tip. Soldering should be carried out from the opposite side of the board to the radial to minimise the risk of damage to the capacitor body. Where possible, a heat sink should be used between the solder joint and the body, especially if longer dwell times are required.

Use of silver loaded epoxy adhesives


Chip capacitors can be mounted to circuit boards using silver loaded adhesive provided the termination material of the capacitor is selected to be compatible with the silver loaded adhesive. This is normally PdAg. Standard tin finishes are often not recommended for use with silver loaded epoxies as there can be electrical and mechanical issues with the joint integrity due to material mismatch.

Solder leaching

Leaching is the term for the dissolution of silver into the solder causing a failure of the termination system which causes increased ESR, tan δ and open circuit faults, including ultimately the possibility of the chip becoming detached. Leaching occurs more readily with higher temperature solders and solders with a high tin content. Pb free solders can be very prone to leaching certain termination systems. To prevent leaching, exercise care when choosing solder alloys and minimize both maximum temperature and dwell time with the solder molten.

Plated terminations with nickel or copper anti leaching barrier layers are available in a range of top coat finishes to prevent leaching occurring. These finishes also include Syfer FlexiCap™ for improved stress resistance post soldering.

Multilayer ceramic chip - with nickel or copper barrier termination




Technical Summary Chip dimensions

Dimensions

Size	Length (L1) mm inches	Width (W) mm inches	Max. Thickness (T) mm inches	Terminati L2 mr inch	2 m
1. 1.12				min	max
0402	1.0 ± 0.10	0.50 ± 0.10	0.60	0.10	0.40
	0.04 ± 0.006	0.02 ± 0.003	0.024	0.004	0.015
0505	1.4 ± 0.38 0.055 ± 0.015	$1.4 \pm 0.25 \\ 0.055 \pm 0.010$	1.27 0.050	0.13 0.005	0.5 0.020
0603	$1.6 \pm 0.2 \\ 0.063 \pm 0.008$	0.8 ± 0.2 0.031 ± 0.008	0.8 0.031	0.10 0.004	0.40 0.015
0805	2.0 ± 0.3	1.25 ± 0.2	1.3	0.13	0.75
	0.08 ± 0.012	0.05 ± 0.008	0.051	0.005	0.03
1111	2.79 + 0.51 - 0.25	2.79 ± 0.38	2.54	0.13	0.63
	0.110 + 0.020 - 0.010	0.110 ± 0.015	0.100	0.005	0.025
1206	3.2 ± 0.3 0.126 ± 0.012	1.6 ± 0.2 0.063 ± 0.008	1.6 0.063	0.25 0.01	0.75 0.03
1210	3.2 ± 0.3 0.126 ± 0.012	2.5 ± 0.3 0.10 ± 0.012	2.0 0.08	0.25 0.01	0.75 0.03
1410	3.6 ± 0.3 0.14 ± 0.012	2.5 ± 0.3 0.10 ± 0.012	2.0 0.08	0.25 0.01	0.75 0.03
1806	4.5 ± 0.35	1.6 ± 0.2	1.3	0.25	0.75
	0.177 ± 0.012	0.063 ± 0.008	0.051	0.01	0.03
1808	4.5 ± 0.35	2.0 ± 0.3	2.0	0.25	1.0
	0.18 ± 0.014	0.08 ± 0.012	0.08	0.01	0.04
1812	4.5 ± 0.35 0.18 ± 0.014	3.2 ± 0.3 0.126 ± 0.012	3.2 0.126	0.25 0.01	1.0 0.04
1825	4.5 ± 0.35	6.30 ± 0.4	4.2	0.25	1.0
	0.18 ± 0.014	0.25 ± 0.016	0.16	0.01	0.04
2211	5.7 ± 0.4	2.79 ± 0.3	2.5	0.25	0.8
	0.225 ± 0.016	0.11 ± 0.012	0.1	0.01	0.03
2215	5.7 ± 0.4	3.81 ± 0.35	2.5	0.25	0.8
	0.225 ± 0.016	0.35 ± 0.02	0.1	0.01	0.03
2220	5.7 ± 0.4	5.0 ± 0.4	4.2	0.25	1.0
	0.225 ± 0.016	0.197 ± 0.016	0.16	0.01	0.04
2225	5.7 ± 0.4	6.3 ± 0.4	4.2	0.25	1.0
	0.225 ± 0.016	0.25 ± 0.016	0.16	0.01	0.04
2520	6.30 ± 0.4	5.0 ± 0.4	4.2	0.25	1.0
	0.25 ± 0.016	0.197 ± 0.016	0.16	0.01	0.04
3640	9.2 ± 0.5	10.16 ± 0.5	4.2	0.5	1.5
	0.36 ± 0.02	0.40 ± 0.02	0.16	0.02	0.06
3820	9.65 ± 0.5	5.0 ± 0.4	4.2	0.5	1.5
	0.37 ± 0.02	0.197 ± 0.016	0.16	0.02	0.06
3035	7.62 ± 0.4	8.90 ± 0.5	4.2	0.5	1.5
	0.30 ± 0.016	0.35 ± 0.02	0.16	0.02	0.06
4045	10.2 ± 0.5	11.5 ± 0.5	4.2	0.5	1.5
	0.40 ± 0.02	0.45 ± 0.02	0.16	0.02	0.06
4545	11.5 ± 0.5	11.5 ± 0.5	4.2	0.5	1.5
	0.45 ± 0.02	0.45 ± 0.02	0.16	0.02	0.06
5550	14.0 ± 0.5	12.7 ± 0.5	4.2	0.5	1.5
	0.55 ± 0.02	0.50 ± 0.02	0.16	0.02	0.06
5868	14.8 ± 0.5	17.3 ± 0.5	4.2	0.5	1.5
	0.58 ± 0.02	0.68 ± 0.02	0.16	0.02	0.06
8040	20.3 ± 0.5	10.16 ± 0.5	4.2	0.5	1.5
	0.80 ± 0.02	0.40 ± 0.02	0.16	0.02	0.06
8060	20.3 ± 0.5	15.24 ± 0.5	4.2	0.5	1.5
	0.80 ± 0.02	0.60 ± 0.02	0.16	0.02	0.06


Custom chip sizes not included in the table, but larger than 2225, can be considered with minimum tooling charges. Please refer specific requests direct to the sales office.

Max thickness relates to standard components and actual thickness may be considerably less. Thicker parts, or components with reduced maximum thickness, can be considered by request – please refer requests to the sales office.



Standard MLCC ranges 10Vdc to 12kVdc Standard MLCC - COG/NPO ranges

A range of dc rated multi-layer chip capacitors from 0.47pF to 22µF and case sizes 0603 to 8060 in COG/NPO and X7R dielectrics. Suitable for all general purpose and high reliability applications where package size and reliability are important. All are manufactured using Syfer's unique wet process and incorporate precious metal electrodes.





Range dimensions - Standard MLCC ranges


Size	Length (L1) mm/inches	Width (W) mm/inches	Max. Thickness (T) mm/inches	Terminat (L: mm/ir	2) nches
0603	1.6 ± 0.2 0.063 ± 0.008	0.8 ± 0.2 0.031 ± 0.008	0.8 0.031	min 0.10 0.004	max 0.40 0.015
0805	2.0 ± 0.3	1.25 ± 0.2	1.3	0.13	0.75
	0.08 ± 0.012	0.05 ± 0.008	0.051	0.005	0.03
1206	3.2 ± 0.3	1.6 ± 0.2	1.6	0.25	0.75
	0.126 ± 0.012	0.063 ± 0.008	0.063	0.01	0.03
1210	3.2 ± 0.3	2.5 ± 0.3	2.0	0.25	0.75
	0.126 ± 0.012	0.1 ± 0.012	0.08	0.01	0.03
1808	4.5 ± 0.35	2.0 ± 0.3	2.0	0.25	1.0
	0.18 ± 0.014	0.08 ± 0.012	0.08	0.01	0.04
1812	4.5 ± 0.35	3.2 ± 0.3	2.5	0.25	1.0
	0.18 ± 0.014	0.126 ± 0.012	0.1	0.01	0.04
1825	4.5 ± 0.35	6.30 ± 0.4	2.5	0.25	1.0
	0.18 ± 0.014	0.25 ± 0.016	0.1	0.01	0.04
2220	5.7 ± 0.4	5.0 ± 0.4	4.2	0.25	1.0
	0.225 ± 0.016	0.197 ± 0.016	0.16	0.01	0.04
2225	5.7 ± 0.4	6.3 ± 0.4	4.2	0.25	1.0
	0.225 ± 0.016	0.25 ± 0.016	0.16	0.01	0.04
3640	9.2 ± 0.5	10.16 ± 0.5	2.5	0.5	1.5
	0.36 ± 0.02	0.4 ± 0.02	0.1	0.02	0.06
5550	14.0 ± 0.5	12.7 ± 0.5	4.2	0.5	1.5
	0.55 ± 0.02	0.5 ± 0.02	0.16	0.02	0.06
8060	20.3 ± 0.5	15.24 ± 0.5	2.5	0.5	1.5
	0.8 ± 0.02	0.6 ± 0.02	0.1	0.02	0.06

Custom chip sizes not included in the table, but larger than 2225, can be considered with minimum tooling charges. Please refer specific requests direct to the sales office. Max thickness relates to standard components and actual thickness may be considerably less. Thicker parts, or components with reduced maximum thickness, can be

Ordering information - Standard MLCC ranges

1210	Υ	100	0103	J	Χ	T	
Chip size	Termination	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric	Packaging	Suffix code
0603 0805 1206 1210 1808 1812 1825 2220 2225 3640 5550 8060	Y = FlexiCap™ termination base with nickel barrier (100% matte tin plating). RoHS compliant. H = FlexiCap™ termination base with nickel barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant. F = Silver Palladium. RoHS compliant. J = Silver base with nickel barrier (100% matte tin plating). RoHS compliant. A = Silver base with nickel barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant.	010 = 10V 016 = 16V 025 = 25V 050 = 50V 063 = 63V 100 = 100V 200 = 250V 500 = 500V 630 = 630V 1KO = 1kV 1K5 = 1.5kV 2K0 = 2kV 2K5 = 2.5kV 3K0 = 3kV 4K0 = 4kV 5K0 = 5kV 6K0 = 6kV 8K0 = 8kV 10K = 10kV 12K = 12kV	<1.0pF Insert a P for the decimal point as the first character. eg. P300 = 0.3pF Values in 0.1pF steps ≥1.0pF & <10pF Insert a P for the decimal point as the second character. eg. 8P20 = 8.2pF Values are E24 series ≥10pF First digit is 0. Second and third digits are significant figures of capacitance code. Fourth digit is number of zeros eg. 0101 = 100pF Values are E24 series	<10pF $H = \pm 0.05 \text{ pF}$ $B = \pm 0.10pF$ $C = \pm 0.25pF$ $D = \pm 0.50pF$ $\geq 10pF$ $F = \pm 1\%$ $G = \pm 2\%$ $J = \pm 5\%$ $K = \pm 10\%$ $M = \pm 20\%$	C = COG/NPO (1B) X = X7R (2R1) P = X5R	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays	Used for specific custome requirements

Standard MLCC - COG/NPO ranges



 Note: The highlighted parts are defined as 'dual-use' under export control legislation and as such are subject to export licence restrictions. Please refer to page 9 for further details.

Note: X7R ranges on reverse

 *These parts may require conformal coating post soldering.
 Standard chip thickness = 2.5mm maximum unless specified as 3.2 or 4.0mm.

Note: X7R ranges on reverse

Note: X7R ranges on reverse

* StackiCap™ high capacitance versions available from the StackiCap[™] range - see page 25 for details.

† Higher capacitance values available from the ProtectiCap™ capacitors range - see page 19 for details.


Note: The highlighted parts are defined as 'dual-use' under export control legislation and as such are subject to export licence restrictions. Please refer to page 9 for further details.

Note: COG/NPO ranges on reverse

ProtectiCap™ capacitors

MLCCs are particularly suitable for high voltage applications where small size is required. For standard high voltage capacitors a coating may be required to be applied post-soldering, to minimise the risk of flashover from one termination on the chip to the other. By contrast, the new ProtectiCap™ high voltage range has been introduced to specifically address this issue. The integral coating minimises the risk of flashover without any requirement for the customer to apply conformal coating after soldering.

This range is fully compliant with the RoHS and WEEE directives. Parts are compatible with lead free solders and standard aqueous and solvent cleaning processes.





Operating Temperature -55°C to +125°C

Temperature Coefficient of Capacitance (Typical) ±15%

Insulation resistance Time constant (Ri xCr) (whichever is the least) $100G\Omega$ or 1000s

Minimum/maximum capacitance values - ProtectiCap™ capacitors

Chip Size	1206	1210	1808	1812	2220
Min Cap	220pF	680pF	330pF	470pF	1.0nF
2000V	3.3nF	5.6nF	5.6nF	12nF	33nF
2500V	2.7nF	4.7nF	4.7nF	8.2nF	22nF
3000V	1.5nF	3.3nF	3.3nF	4.7nF	10nF
4000V	-	-	2.2nF	3.3nF	6.8nF
5000V	-	-	-	-	4.7nF
7" Reel	2,500	2,000	1,500	500/1,000*	500/1,000*
13" Reel	10,000	8,000	6,000	2,000/4,000*	2,000/4,000*

NOTE: Other capacitance values may become available, please contact the sales office if you need values other than those shown in the above table. For dimensions and soldering information, please go to our website (www.syfer.com) or see our MLC Catalogue. *Reel quantity depends on chip thickness. Please contact sales office.

Ordering information - ProtectiCap™ capacitors


1206	Р	2K0	0102	K	X	T
Chip size	Termination	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric	Packaging
1206 1210 1808 1812 2220	P = ProtectiCap™ (FlexiCap™ termination base with Ni barrier, 100% matte tin plating).	2KO = 2kV 2K5 = 2.5kV 3KO = 3kV 4KO = 4kV 5KO = 5kV	First digit is 0. Second and third digits are significant figures of capacitance code. The fourth digit is number of 0's following Example 0102 = 1000pF	$J = \pm 5\%$ $K = \pm 10\%$ $M = \pm 20\%$	X = X7R	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays




Note: COG/NPO ranges on reverse Note: COG/NPO ranges on reverse

TCC/VCC range

X7R capacitors are available from Syfer with a defined capacitance variation under applied dc voltage, across the full operating temperature range. Whilst the capacitance of COG/NPO chips does not vary with applied voltage, standard X7R capacitors exhibit capacitance fluctuation but with no specified limit. For applications where a limit is required, Syfer is able to offer either a "B" code dielectric (conforms to MIL "BX" dielectric and IECQ-CECC "2X1") or "R" code dielectric (conforms to MIL "BZ" dielectric and IECQ-CECC "2C1").



TCC/VCC capacitors - 2C1 (BZ)




■ = non RoHS compliant and FlexiCap™ termination only. Other values available in J, Y (FlexiCap™) and F terminations.

		X7R				
Dielectric characteristics		Stable				
IECQ-CECC	2C1	2R1	2X1			
EIA	-	X7R	-			
MIL	BZ	-	ВХ			
Rated temperature range		-55°C to +125°C				
Maximum capacitance change over temperature range No DC voltage applied	±20%	±15%	±15%			
Rated DC voltage applied	+20-30%	-	+15-25%			
Syfer dielectric ordering code	R	Х	В			

For part numbering, the "X" denoting the X7R dielectric code needs to be replaced by either "B" or "R". Please contact the sales office for full range information.

TCC/VCC capacitors - 2X1 (BX)



■ = non RoHS compliant and FlexiCap™ termination only. Other values available in J, Y (FlexiCap™) and F terminations.

CapCad ™ capacitor modelling software is now available for the HiQ range. This software has been developed with an easy to use and readily accessible comparison tool for choosing the best MLCC to suit the customer's needs. Please consult the Syfer website to launch the software.


Operating Temperature -55°C to +125°C

Temperature Coefficient (Typical)

0 ± 30 ppm/°C

Insulation resistance at +25°C

>100GΩ



Insulation resistance at +125°C

Minimum/maximum capacitance values - High Q capacitors - MS range

Chip Size	0402*	0603	0505	0805	1206	1111	1210	1812	2220	2225	3640
Min Cap	0.1pF	0.1pF	0.2pF	0.2pF	0.5pF	0.3pF	0.3pF	1.0pF	2.0pF	2.0pF	4.0pF
50V _{63V}	33pF	220pF	330pF	680pF	2.2nF						
100V	22pF	150pF	220pF	470pF	1.5nF	3.3nF	3.3nF	6.8nF	15nF	18nF	
150V	18pF	120pF	180pF	390pF	1.2nF	2.7nF	2.7nF	4.7nF	12nF	15nF	
^{200V} 250V	15pF	100pF	150pF	330pF	1.0nF	2.2nF	2.2nF	3.9nF	10nF	10nF	
300V		56pF	100pF	220pF	680pF	1.5nF	1.5nF	3.3nF	6.8nF	8.2nF	
500V				100pF	330pF	820pF	820pF	2.2nF	4.7nF	5.6nF	15nF
630V					150pF	390pF	390pF	1.0nF	2.2nF	3.3nF	6.8nF
1000V					82pF	220pF	220pF	680pF	1.5nF	2.2nF	4.7nF
2000V					18pF	68pF	68pF	150pF	470pF	560pF	1.5nF
3000V								68pF	150pF	220pF	470pF
Tape	7" reel 5000	7" reel 4000	7" reel 2500	7" reel 3000	7" reel 2500	7" reel 1000	7" reel 2000	7" reel 500/1000	7" reel 500/1000	7" reel 500/1000	7" reel n/a
quantities		13" reel quantities available on request					13" reel 2000/4000	13" reel 2000/4000	13" reel 2000/4000	13" reel n/a	

Below 1pF capacitance values are available in 0.1pF steps.

Above 1pF capacitance values are available in 0.1pr steps.

Above 1pF capacitance values are available in E24 series values.

Other values and taping quantities may be available on request, consult the Sales Office for details.

For values < than 0.3pF please consult the Sales Office for availability.

*0402 - please consult the Sales Office for availability.


Ordering information - High Q capacitors - MS range

0505	J	250	4P70	В	Q	Т
Chip size	Termination	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric	Packaging
0402* 0603 0505 0805 1206 1111 1210 1812 2220 2225 3640	Y = FlexiCap™ termination base with nickel barrier (100% matte tin plating). RoHS compliant. Lead free. H = FlexiCap™ termination base with nickel barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant. J = Silver base with nickel barrier (100% matte tin plating). RoHS compliant. Lead free. A = Silver base with nickel barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant.	050 = 50V 063 = 63V 100 = 100V 150 = 150V 200 = 200V 250 = 250V 300 = 300V 500 = 500V 630 = 630V 1K0 = 1kV 2K0 = 2kV 3K0 = 3kV	<1.0pF Insert a P for the decimal point as the first character. eg. P300 = 0.3pF Values in 0.1pF steps ≥1.0pF & <10pF Insert a P for the decimal point as the second character. eg. 8P20 = 8.2pF Values are E24 series ≥10pF First digit is 0. Second and third digits are significant figures of capacitance code. Fourth digit is number of zeros eg. 0101 = 100pF Values are E24 series	$<4.7 pF \\ H = \pm 0.05 pF \\ B = \pm 0.1 pF \\ C = \pm 0.25 pF \\ D = \pm 0.5 pF \\ <10 pF \\ B = \pm 0.1 pF \\ C = \pm 0.25 pF \\ \ge 10 pF \\ E = \pm 1.9 \\ G = \pm 2.9 \\ J = \pm 5.9 \\ K = \pm 10.9 $	Q = High Q Ceramic	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays


*0402 - please consult the sales office for availability


Typical performance data - 0805 chip size*


MS range





Typical performance data - 1111 chip size*











^{*} Please refer to the sales office for other chip size electrical data.

The Ultra-low ESR range offers a very stable, High Q material system that provides excellent, low loss performance in systems below 3GHz.

Available with various termination options including FlexiCap™, this range of high frequency capacitors is suitable for many applications where economical, high performance is required.

Operating Temperature -55°C to +125°C


Temperature Coefficient (Typical)

 0 ± 30 ppm/°C

Insulation resistance

Time constant (Ri xCr) (whichever is the least)

 $100G\Omega$ or 1000s




Minimum/maximum capacitance values - Ultra-low ESR capacitors

Chip Size	0505	0603	0805	1111
Min Cap	0.8pF	0.5pF	0.8pF	0.7pF
200V _{250V}	150pF	100pF	240pF	-
500V	-	-	-	240pF
Tono quantities	7" reel - 2,500	7" reel - 4,000	7" reel - 3,000	7" reel - 1,000
Tape quantities	13" reel - 10,000	13" reel - 16,000	13" reel - 12,000	13" reel - 5,000

Note: Below 1pF capacitance values are available in 0.1pF steps. Above 1pF capacitance values are available in E24 series values. Other values and taping quantities may be available on request, consult the sales office for details.

Typical performance - 0805 chip size



Ordering information - Ultra-low ESR capacitors

0805	J	250	0101	J	U	Т
Chip size	Termination	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric	Packaging
0505 0603 0805 1111	Y = FlexiCap™ termination base with nickel barrier (100% matte tin plating). RoHS compliant. Lead free. H = FlexiCap™ termination base with nickel barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant. J = Silver base with nickel barrier (100% matte tin plating). RoHS compliant. Lead free. A = Silver base with nickel barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant.		<1.0pF Insert a P for the decimal point as the first character. eg. P300 = 0.3pF Values in 0.1pF steps ≥1.0pF & <10pF Insert a P for the decimal point as the second character. eg. 8P20 = 8.2pF Values are E24 series ≥10pF First digit is 0. Second and third digits are significant figures of capacitance code. Fourth digit is number of zeros eg. 0101 = 100pF Values are E24 series	$<4.7 pF \\ H = \pm 0.05 pF \\ B = \pm 0.1 pF \\ C = \pm 0.25 pF \\ D = \pm 0.5 pF \\ < 10 pF \\ B = \pm 0.1 pF \\ C = \pm 0.25 pF \\ \geq 10 pF \\ E = \pm 1\% \\ G = \pm 2\% \\ J = \pm 5\% \\ K = \pm 10\%$	U = Ultra-low ESR	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays

The StackiCap™ range offers a significant reduction in 'PCB real estate' for an equivalent capacitance value when board space is at a premium.

Syfer's unique patent pending* construction and FlexiCap™ termination material make the StackiCap™ range suitable for applications including: power supplies, lighting, aerospace electronics and high voltage applications where a large amount of capacitance is required. Further developments are on-going, please contact the Sales Office for details of the full range.

* Patent application No. 1210261-2 applies.

Maximum capacitance Up to 5.6μF Maximum voltage Up to 2kV



Comparison chart - StackiCap™ capacitors

Chip Size	Voltage	StackiCap™ range (nF)	Non- StackiCap™ range (nF)	Replaces Case Size
	200/250V	1000	680	2220
	500V	470	330	2220
1812	630V	330	180	2220
1012	1kV	180	100	2225 / 3640
	1.2kV	100	33	2225
	1.5kV	56	22	2225
	200/250V	2200	1000	3640
	500V	1000	560	3640
	630V	1000	330	5550
2220	1kV	470	120	8060
	1.2kV	220	82	5550
	1.5kV	150	47	5550
	2kV	100	27	8060
	200/250V	5600	3300	5550
	500V	2700	1000	8060
	630V	2200	680	8060
3640	1kV	1000	180	8060
	1.2kV	470	150	8060
	1.5kV	330	100	8060
	2kV	150	47	8060

Ordering information - StackiCap™ capacitors

1812	Y	500	0474	J	X	Т	WS2
Chip size	Termination	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric	Packaging	Suffix code
1812 2220 3640	Y = FlexiCap™ termination base with nickel barrier (100% matte tin plating). RoHS compliant. Lead free. H = FlexiCap™ Termination base with nickel barrier (Tin/lead plating with minimum 10% lead). Not RoHS compliant.	200/250 = 200/250V 500 = 500V 630 = 630V 1K0 = 1kV 1K2 = 1.2kV 1K5 = 1.5kV 2K0 = 2kV	First digit is 0. Second and third digits are significant figures of capacitance code in picofarads (pF). Fourth digit is number of zeros eg. 0474 = 470nF Values are E12 series	$J = \pm 5\%$ $K = \pm 10\%$ $M = \pm 20\%$	X = X7R	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays	WS2

Reeled quantities - StackiCap™ capacitors

	1812	2220	3640
178mm (7") Reel	500/1,000	500/1,000	-
330mm (13") Reel	2,000/4,000	2,000/4,000	500



However, RoHS requirements have dictated the use of lead-free solders, and the composition of these solders has resulted in an increase in soldering temperatures. This has caused solder leaching problems for the Ag/Pd termination, and meant alternative terminations have had to be found.

As copper is non-magnetic, one solution is to use a copper barrier instead of a nickel barrier, with a tin finish on top and this is the solution Syfer has developed.

This Non-magnetic termination is offered with selected non-magnetic COG/NPO, High Q and X7R dielectrics, providing a fully non-magnetic component (μ r = 1.0000).

To meet high temperature 260°C soldering reflow



profiles as detailed in J-STD-020, COG/NPO dielectrics are supplied with FlexiCap™ or sintered termination and X7R dielectrics are supplied with Syfer's award winning FlexiCap™ termination.

COG/NPO & High Q - minimum/maximum capacitance values

Chip Size	0402*	0603	0505	0805	1206	1111 1210	1808	1812	2220	2225
Min Cap	0.1pF	0.1pF	0.2pF	0.2pF	0.5pF	0.3pF	1.0pF	1.0pF	2.0pF	2.0pF
Min Cap Tolerance			±0.05pF (<4.7pF), 0	.1pF (<u>></u> 4.7	pF & <10pl	=) and ±1%	% (<u>≥</u> 10pF)		
50V _{63V}	22pF	100pF	220pF	470pF	1.5nF	-	-	-	-	-
100V	15pF	68pF	150pF	330pF	1.0nF	2.2nF	2.2nF	4.7nF	10nF	15nF
150V	10pF	47pF	100pF	220pF	680pF	1.5nF	1.5nF	3.3nF	6.8nF	10nF
200V _{250V}	6.8pF	33pF	56pF	150pF	470pF	1.0nF	1.0nF	2.2nF	4.7nF	6.8nF
300V	-	27pF	47pF	120pF	390pF	820pF	820pF	1.8nF	3.9nF	5.6nF
500V	-	-	-	68pF	270pF	680pF	680pF	1.5nF	3.3nF	4.7nF
630V	-	-	-	-	150pF	390pF	390pF	1.0nF	2.2nF	3.3nF
1000V	-	-	-	-	82pF	220pF	220pF	680pF	1.5nF	2.2nF
2000V	-	-	-	-	18pF	68pF	68pF	150pF	470pF	560pF
3000V	-	-	-	-	-	-	-	68pF	150pF	220pF

For values < than 0.3pF please consult the Sales Office for availability. *0402 - please consult the sales office for availability.

X7R - minimum/maximum capacitance values

X/R - minimum/m	aximum c	apacitan	ce values						
Chip Size	0402*	0603	0805	1206	1210	1808	1812	2220	2225
Min Cap	47pF	100pF	330pF	680pF	1.5nF	2.2nF	3.3nF	6.8nF	10nF
Min Cap Tolerance					±5%				
16V	10nF	100nF	330nF	1.0µF	1.5µF	1.5µF	3.3µF	5.6µF	6.8µF
25V	6.8nF	68nF	220nF	820nF	1.2µF	1.2µF	2.2µF	4.7µF	5.6µF
50V _{63V}	4.7nF	47nF	150nF	470nF	1.0µF	680nF	1.5µF	3.3µF	3.3µF
100V	1.5nF	10nF	47nF	150nF	470nF	330nF	1.0µF	1.5µF	1.5µF
200V _{250V}	680pF	5.6nF	27nF	100nF	220nF	180nF	470nF	1.0µF	1.0µF
500V	-	1.5nF	8.2nF	33nF	100nF	100nF	270nF	560nF	680nF
630V	-	-	4.7nF	10nF	27nF	33nF	150nF	330nF	390nF
1000V	-	-	3.3nF	4.7nF	15nF	18nF	56nF	120nF	150nF
1200V	-	-	-	3.3nF	10nF	10nF	33nF	82nF	100nF
1500V	-	-	-	2.7nF	6.8nF	6.8nF	22nF	47nF	68nF
2000V	_	_	_	2.2nF	4.7nF	4.7nF	10nF	27nF	33nF

*0402 - please consult the factory for availability.

26

Ordering information - Non-magnetic capacitors

1210	3	100	0103	J	Χ	T	
Chip size	Termination	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric codes	Packaging	Suffix code
0402* 0603 0505 0805 1206 1111 1210 1808 1812 2220 2225	2 = Sintered silver base with copper barrier (100% matte tin plating). RoHS compliant. (Available on COG/NPO & High Q only). 3 = FlexiCap™ base with copper barrier (100% matte tin plating). RoHS compliant. 4 = Sintered silver base with copper barrier (tin/lead plating). Non RoHS compliant. (Available on COG/NPO & High Q only). 5 = FlexiCap™ base with copper barrier (tin/lead plating). Non RoHS compliant.	016 = 16V 025 = 25V 050 = 50V 063 = 63V 100 = 100V 150 = 150V 200 = 200V 250 = 250V 500 = 500V 630 = 630V 1K0 = 1kV 1K2 = 1.2kV 1K5 = 1.5kV 2K0 = 2kV 3K0 = 3kV	<10pF Insert a P for the decimal point, eg. P300 = 0.3pF, 8P20 = 8.2pF. ≥10pF 1st digit is 0. 2nd and 3rd digits are significant figures of capacitance code. The 4th digit is number of 0's following eg. 0103 = 10000pF Values <1pF in 0.1pF steps, above this values are E24 series	$<4.7pF \\ H = \pm 0.05pF \\ B = \pm 0.1pF \\ C = \pm 0.25pF \\ D = \pm 0.5pF \\ \ge 4.7pF \\ \ge 4.7pF \\ B = \pm 0.1pF \\ C = \pm 0.25pF \\ D = \pm 0.5pF \\ \ge 10pF \\ F = \pm 1\% \\ G = \pm 2\% \\ J = \pm 5\% \\ K = \pm 10\% \\ M = \pm 20\% \\ \label{eq:mass_problem}$	C = COG/NPO (1B) Q = High Q X = X7R (2R1)	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays	Used for specific customer requirements

*0402 - please consult the sales office for availability.


Reeled Quantities


Chip Size	0402*	0603	0505	0805	1206	1111 1210	1808	1812	2220	2225
7" Reel	5000	4000	2500	3000	2500	1000 ₂₀₀₀	2000	500/1000	500/1000	500/1000
13" Reel		13" reel quantities available on request						2000/4000	2000/4000	2000/4000


Note: Other capacitance values may become available, please contact our Sales Office if you need values other than those shown in the above tables. For dimensions and soldering information, please go to our website (www.svfer.com) or see our MLC catalogue.


Typical performance data - 0805 chip size


Typical performance data - 1111 chip size











Capacitance values

2pF to 10nF (High Q)

Chip sizes

2225 and 4040

Operating temperature

-55°C to +125°C

High Q low ESR dielectrics

(other options available)

Insulation Resistance (IR)

100Gohm min @ 100 Vdc or 1000s (whichever is the less)

DWV up to 8400Vdc


Termination material


Silver plated copper ribbon attached with HMP solder (MP greater than 260°C)




2225


28











Ordering information - Non-magnetic Ribbon Leaded capacitors

4040	В	7 K0	0470	G	Q	В	Lead options	Variant code
Chip size	Coating	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric	Packing	R	W001
2225 4040	B = Uncoated	200 = 200V 500 = 500V 1K0 = 1kV 2K0 = 2kV 3K0 = 3kV 5K0 = 5kV 7K0 = 7kV	<10pF Insert a P for the decimal point, eg 2P20 = 2.2pF. >10pF. 1st digit is 0. 2nd and 3rd digits are significant figures of capacitance code. The 4th digit is number of 0's following eg. 0470 = 47pF 0512 = 5100pF	<10pF $B = \pm 0.10pF$ $C = \pm 0.25pF$ $D = \pm 0.50pF$ $\geqslant 10pF$ $G = \pm 2\%$ $J = \pm 5\%$ $K = \pm 10\%$ $M = \pm 20\%$	C = COG/NPO (1B) Q = High Q X = X7R (2R1)	B = Bulk packed	R = Ribbon Leaded	W001 = Standard Variant

Open Mode capacitors have been designed specifically for use in applications where mechanical cracking is a severe problem and short circuits due to cracking are unacceptable.

Open Mode capacitors use inset electrode margins, which prevent any mechanical cracks which may form during board assembly from connecting to the internal electrodes.

When combined with Syfer's FlexiCap™ termination, Syfer Open Mode capacitors provide a robust component with the assurance that if a part becomes cracked, the crack will be unlikely to result in short circuit failure.

Open Mode max capacitance (X7R only)

	0603	0805	1206	1210	1808	1812	2220	2225
16V	39nF	150nF	470nF	680nF	680nF	1.5µF	3.3µF	4.7µF
25V	33nF	120nF	330nF	560nF	560nF	1.2µF	2.2µF	3.9µF
50/63V	22nF	100nF	220nF	470nF	470nF	1.0µF	1.5µF	2.7µF
100V	6.8nF	27nF	100nF	220nF	220nF	680nF	1.0µF	1.8µF
200/ 250V	2.7nF	15nF	68nF	100nF	100nF	330nF	680nF	1.0µF
500V	-	5.6nF	27nF	68nF	68nF	180nF	330nF	330nF
630V	-	-	10nF	27nF	27nF	82nF	180nF	180nF
1kV	-	-	4.7nF	15nF	15nF	33nF	82nF	100nF

= AEC-Q200

X7R


Tandem Capacitors have been designed as a fail safe range using a series section internal design, for use in any application where short circuits would be unacceptable.

When combined with Syfer's FlexiCap™ termination, Syfer Tandem capacitors provide an ultra robust and reliable component, for use in the most demanding applications. Non-standard voltages are available. For more information please consult the sales office.


Tandem max capacitance (X7R only)

	0603	0805	1206	1210	1812	2220	2225
16V	12nF	47nF	150nF	270nF	560nF	1.2µF	1.5µF
25V	10nF	39nF	120nF	220nF	470nF	1.0µF	1.2µF
50/63V	6.8nF	33nF	100nF	180nF	390nF	680nF	1.0µF
100V	2.2nF	10nF	47nF	82nF	220nF	470nF	680nF
200/ 250V	1.0nF	4.7nF	22nF	47nF	100nF	220nF	330nF

= AEC-Q200



Qualification included cracking the components by severe bend tests. Following the bend tests cracked components were subjected to endurance / humidity tests, with no failures evident due to short circuits. Note: Depending on the severity of the crack, capacitance loss was between 0% and 70%.



Qualification included cracking the components by severe bend tests. Following the bend tests cracked components were subjected to endurance / humidity tests, with no failures evident due to short circuits. Note: Depending on the severity of the crack, capacitance loss was between 0% and 50%.

Ordering information - Open Mode and Tandem capacitors

1206	Υ	050	0224	K	X	Т	
Chip size	Termination	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric codes	Packaging	Suffix code
0603 0805 1206 1210 1808 1812 2220 2225	Y = FlexiCap™ termination base with nickel barrier (100% matte tin plating). RoHS compliant.	016 = 16V 025 = 25V 050 = 50V 063 = 63V 100 = 100V 200 = 200V 250 = 250V 500 = 500V 630 = 630V 1KO = 1kV	First digit is 0. Second and third digits are significant figures of capacitance code. The fourth digit is number of zeros following. Example: 0224 = 220000pF	$J = \pm 5\%$ $K = \pm 10\%$ $M = \pm 20\%$	X = X7R E = X7R (AEC-Q200 product)	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays	M01 = Syfer Open Mode capacitor T01 = Syfer Tandem capacitor

IECQ-CECC, AEC-Q200 and Space grade range

A range of specialist, high reliability, multilayer ceramic capacitors for use in critical or high reliability environments. All fully tested / approved and available with a range of suitable termination options, including tin/lead plating and Syfer FlexiCap™.

Ranges include :-

- 1. Range tested and approved in accordance with IECQ-CECC QC32100.
- 2. Range qualified to the requirements of AEC-Q200.
- 3. Range qualified to the requirements of Syfer detail specification S02A-0100 (based on ESCC 3009).



IECQ-CECC - maximum capacitance values

		0603	0805	1206	1210	1808	1812	2220	2225
1/1/	COG/NPO	1.5nF	6.8nF	22nF	33nF	33nF	100nF	150nF	220nF
16V	X7R	100nF	330nF	1.0µF	1.5µF	1.5µF	3.3µF	5.6µF	6.8µF
25V	COG/NPO	1.0nF	4.7nF	15nF	22nF	27nF	68nF	100nF	150nF
23 V	X7R	56nF	220nF	820nF	1.2µF	1.2µF	2.2µF	4.7µF	5.6µF
50/63V	COG/NPO	470pF	2.7nF	10nF	18nF	18nF	33nF	68nF	100nF
30/03V	X7R	47nF	220nF	470nF	1.0µF	680nF	1.5µF	2.2µF	3.3µF
100V	COG/NPO	330pF	1.8nF	6.8nF	12nF	12nF	27nF	47nF	68nF
1000	X7R	10nF	47nF	150nF	470nF	330nF	1.0µF	1.5µF	1.5µF
200/	COG/NPO	100pF	680pF	2.2nF	4.7nF	4.7nF	12nF	22nF	27nF
250V	X7R	5.6nF	27nF	100nF	220nF	180nF	470nF	1.0µF	1.0µF
500V	COG/NPO	n/a	330pF	1.5nF	3.3nF	3.3nF	10nF	15nF	22nF
300V	X7R	n/a	8.2nF	33nF	100nF	100nF	270nF	560nF	820nF
1kV	COG/NPO	n/a	n/a	470pF	1.0nF	1.2nF	3.3nF	8.2nF	10nF
IKV	X7R	n/a	n/a	4.7nF	15nF	18nF	56nF	120nF	150nF

Ordering information - IECQ-CECC range

1210	Υ	100	0103	J	D	Т	
Chip size	Termination	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric Release codes	Packaging	Suffix code
0603 0805 1206 1210 1808 1812 2220 2225	Y = FlexiCap [™] termination base with Ni barrier (100% matte tin plating). RoHS compliant. H = FlexiCap [™] termination base with Ni barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant. F = Silver Palladium. RoHS compliant. J = Silver base with nickel barrier (100% matte tin plating). RoHS compliant. A = Silver base with nickel barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant.	016 = 16V 025 = 25V 050 = 50V 063 = 63V 100 = 100V 200 = 200V 250 = 250V 500 = 500V 1KO = 1kV	First digit is 0. Second and third digits are significant figures of capacitance code. The fourth digit is number of zeros following Example: 0103 = 10nF	<10pF $B = \pm 0.1pF$ $C = \pm 0.25pF$ $D = \pm 0.5pF$ $\geq 10pF$ $F = \pm 1\%$ $G = \pm 2\%$ $J = \pm 5\%$ $K = \pm 10\%$ $M = \pm 20\%$	D = X7R (2R1) with IECQ- CECC release F = COG/NPO (1B/NPO) with IECQ- CECC release B = 2X1/BX released in accordance with IECQ-CECC R = 2C1/BZ released in accordance with IECQ-CECC For B and R codes please refer to TCC/ VCC range for full capacitance values	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays	Used for specific customer require- ments

AEC-Q200 range - maximum capacitance values

Speciality High Rel. and approved parts

		0603	0805	1206	1210	1812
F0// 2V/	COG/NPO	470pF	2.7nF	10nF	18nF	39nF
50/63V	X7R	33nF	150nF	330nF	680nF	1.5µF
100V	COG/NP0	330pF	1.8nF	6.8nF	12nF	27nF
1000	X7R	10nF	47nF	150nF	470nF	1.0μF
200/	COG/NPO	100pF	680pF	2.2nF	4.7nF	12nF
250V	X7R	5.6nF	27nF	100nF	220nF	470nF
500V	COG/NPO	n/a	330pF	1.5nF	3.9nF	10nF
300V	X7R	n/a	8.2nF	33nF	100nF	270nF
630V	COG/NP0	n/a	n/a	1.0nF	1.8nF	5.6nF
630V	X7R	n/a	n/a	10nF	27nF	150nF
1kV	COG/NPO	n/a	n/a	470pF	1.0nF	3.3nF
TKV	X7R	n/a	n/a	4.7nF	15nF	56nF

Ordering information - AEC-Q200

1210	Υ	100	0103	J	E	Т	
Chip size	Termination	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric Release codes	Packaging	Suffix code
0603 0805 1206 1210 1812	Y = FlexiCap™ termination base with Ni barrier (100% matte tin plating). RoHS compliant. H = FlexiCap™ termination base with Ni barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant. J = Silver base with nickel barrier (100% matte tin plating). RoHS compliant. A = Silver base with nickel barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant. Available in COG/NPO only.	050 = 50V 063 = 63V 100 = 100V 200 = 200V 250 = 250V 500 = 500V 630 = 630V 1KO = 1kV	First digit is 0. Second and third digits are significant figures of capacitance code. The fourth digit is number of zeros following Example: 0103 = 10nF	<10pF $B = \pm 0.1pF$ $C = \pm 0.25pF$ $D = \pm 0.5pF$ $\geq 10pF$ $F = \pm 1\%$ $G = \pm 2\%$ $J = \pm 5\%$ $K = \pm 10\%$ $M = \pm 20\%$	E = X7R (2R1) AEC-Q200 A = COG/NP0 (1B/NP0) AEC-Q200	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays	Used for specific customer require- ments

3 Terminal EMI Components (E01) - AEC-Q200 range - maximum capacitance values

		0805	1206	1806
EOV.	COG/NP0	820pF	1.0nF	2.2nF
50V	X7R	47nF	100nF	200nF
1001/	COG/NP0	560pF	1.0nF	2.2nF
100V	X7R	15nF	15nF	68nF

Note: For some lower capacitance parts, higher voltage rated parts may be supplied. Please refer to page 40.

X2Y Integrated Passive Components (E03) - AEC-Q200 range - min./max. capacitance values

		0805	1206	1410	1812
50V	COG/NPO	390pF - 470pF	1.2nF - 1.5nF	4.7nF - 5.6nF	8.2nF - 10nF
30V	X7R	18nF - 33nF	56nF - 150nF	180nF - 330nF	390nF- 560nF
1001/	COG/NPO	10pF - 330pF	22pF - 1.0nF	100pF - 3.9nF	820pF - 6.8nF
100V	X7R	470pF - 15nF	1.5nF - 47nF	4.7nF - 150nF	8.2nF - 330nF

Note: For some lower capacitance parts, higher voltage rated parts may be supplied. Please refer to page 42.

S02A Space grade range - minimum/maximum capacitance values

		0603	0805	1206	1210	1812	2220	2225
16V	COG/ NPO	390pF - 1.5nF	1pF - 6.8nF	1pF - 22nF	10pF - 33nF	220pF - 100nF	470pF - 150nF	560pF - 220nF
100	X7R	330pF - 100nF	100pF - 330nF	680pF - 1.0μF	1.0nF - 1.5µF	3.9nF - 3.3µF	10nF - 5.6μF	18nF - 6.8µF
25V	COG/ NPO	390pF - 1.0nF	1pF - 4.7nF	1pF - 15nF	10pF - 22nF	220pF - 68nF	470pF - 100nF	560pF - 150nF
23 V	X7R	330pF - 56nF	100pF - 220nF	680pF - 820nF	1.0nF - 1.2µF	3.9nF - 2.2µF	10nF - 4.7μF	18nF - 5.6μF
50/63V	COG/ NPO	0.5pF - 470pF	1pF - 2.7nF	1pF - 10nF	10pF - 18nF	220pF - 39nF	470pF - 68nF	560pF - 100nF
30/03 V	X7R	330pF - 47nF	100pF - 220nF	680pF - 470nF	1.0nF - 1.0μF	3.9nF - 2.2µF	10nF - 3.3μF	18nF - 3.3μF
100V	COG/ NPO	1pF - 330pF	1pF - 1.8nF	1pF - 6.8nF	10pF - 12nF	220pF - 27nF	470pF - 47nF	560pF - 68nF
100 V	X7R	100pF - 10nF	100pF - 47nF	100pF - 150nF	1.0nF - 470nF	3.9nF - 1.0μF	10nF - 1.5μF	18nF - 1.5μF
200V	COG/ NPO	1pF - 100pF	1pF - 680pF	1pF - 2.2nF	10pF - 4.7nF	220pF - 12nF	470pF - 22nF	560pF - 27nF
200 V	X7R	100pF - 5.6nF	100pF - 27nF	100pF - 100nF	1.0nF - 220nF	3.9nF - 470nF	10nF - 1.0μF	18nF - 1.0μF
500V	COG/ NPO	-	1pF - 270pF	1pF - 1.2nF	10pF - 2.7nF	180pF - 6.8nF	390pF - 15nF	4.7nF - 18nF
300 V	X7R	-	10pF - 8.2nF	180pF - 33nF	390pF - 100nF	390pF - 270nF	1nF - 560nF	15nF - 820nF

Note: In accordance with ESCC 3009.

Ordering information - S02A Space grade range - product code construction

1210	Α	100	0103	J	X	T		
Chip size	Termination ⁽¹⁾	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric Rel Release codes	Packaging	Suffix code	
0603 0805 1206 1210 1812 2220 2225	Y = FlexiCap™ termination base with nickel barrier (100% matte tin plating). RoHS compliant. H = FlexiCap™ termination base with nickel barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant. F = Silver Palladium. RoHS compliant. A = Silver base with nickel barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant. Available in COG/NPO only.	016 = 16V 025 = 25V 050 = 50V 063 = 63V 100 = 100V 200 = 200V 500 = 500V	First digit is 0. Second and third digits are significant figures of capacitance code. The fourth digit is number of zeros following Example: 0103 = 10nF	$<10pF \\ B = \pm 0.1pF \\ C = \pm 0.25pF \\ D = \pm 0.5pF \\ \ge 10pF \\ F = \pm 1\% \\ G = \pm 2\% \\ J = \pm 5\% \\ K = \pm 10\% \\ M = \pm 20\% \\$	C = COG/NPO (1B) X = X7R (2R1)	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays Q = Waffle pack	Used for specific customer requirements SO2A = S (Space Grade) High Rel	

- (1) Termination A, H & F available for Space applications. If another termination type is required then contact the sales office.
- (2) Please include Lot Acceptance Test requirement (LAT1, LAT2 or LAT3) on purchase order against each line item. Tests conducted after 100% Burn-In (2xRV @125°C for 168 hours).

LAT1: 4 x adhesion, 8 x rapid temp change + LAT2 and LAT3.

LAT2: 20 x 1000 hour life test + LAT3.

LAT3: 6 x TC and 4 x solderability.

(3) SO2A Space Grade Options

S02A: with LAT1 (also incorporates LAT2 & LAT3). S02A: with LAT2 (also incorporates LAT3).

S02A: with LAT3.

S02A: No LAT conducted.

S02A5: S02A design with 100% visual inspection and 100% electrical test verification.

No screening tests (including no burn in).


No LAT tests etc. These are typically ordered for Engineering Models.

Safety Certified capacitors

Syfer Technology's Safety Certified capacitors comply with international UL and TÜV specifications to offer designers the option of using a surface mount ceramic multilayer capacitor to replace leaded film types. Offering the benefits of simple pick-and-place assembly, reduced board space required and lower profile, they are also available in a FlexiCap™ version to reduce the risk of mechanical cracking.

Syfer's high voltage capacitor expertise means the range offers among the highest range available of capacitance values in certain case sizes. Applications include: modems, AC-DC power supplies and where lightning strike or other voltage transients represent a threat to electronic equipment.


- Surface mount multilayer ceramic capacitors
- Meet Class Y2/X1, Y3/X2 and X2 requirements
- Approved for mains ac voltages, up to 250Vac
- Approved by UL and TÜV
- Sizes 1808, 1812, 2211, 2215 and 2220
- Smaller sizes suitable for use in equipment certified



- Certification specifications for larger sizes include IEC/ EN60384-14, UL/CSA60950 and UL60384-14
- Surface mount package
- Reduces board area and height restrictions
- Reduced assembly costs over conventional through hole components
- FlexiCap™ option available on all sizes

Class	Rated voltage	Impulse voltage	Insulation bridging	May be used in primary circuit
Y1	250Vac	8000V	Double or reinforced	Line to protective earth
Y2	250Vac	5000V	Basic or supplementary*	Line to protective earth
Y3	250Vac	None	Basic or supplementary	-
Y4	150Vac	2500V	Basic or supplementary*	Line to protective earth
X1	250Vac	4000V	-	Line to line
X2	250Vac	2500V	-	Line to line
Х3	250Vac	None	-	Line to line

^{* 2} x Y2 or Y4 rated may bridge double or reinforced insulation when used in series.



Classification and approval specification - Safety Certified capacitors

CHIP SIZE	DIELECTRIC	CAP RANGE	SYFER FAMILY CODE	CLASSIFICATION	APPROVAL SPECIFICATION	APPROVAL BODY
1808	C0G/NP0	4.7pF to 1.5nF	SP ⁽¹⁾	Y3/X2 ⁽⁶⁾ NWGQ2, NWGQ8	IEC60384-14:2005 EN60384-14:2005 	TÜV ——— UL
1808	X7R	150pF to 4.7nF	SP ⁽¹⁾	Y3/X2 ⁽⁶⁾ NWGQ2, NWGQ8	CSA 60950-1-07 2nd Ed IEC60384-14:2005 EN60384-14:2005 UL-60950-1, 2nd Ed	TÜV UL
1808	COG/NP0	4.7pF to	(1)	Y2/X1 ⁽⁶⁾ NWGQ2, NWGQ8	CSA 60950-1-07 2nd Ed IEC60384-14:2005 EN60384-14:2005 UL-60950-1, 2nd Ed	TÜV
1808	X7R	390pF 150pF to	(1,3)	Y2/X1 ⁽⁶⁾	CSA 60950-1-07 2nd Ed IEC60384-14:2005 EN60384-14:2005 UL-60950-1, 2nd Ed	TÜV
1812	C0G/NP0	1.5nF 4.7pF to	NWGQ2, NWGQ8 (1) Y2/X1 (6) NWGQ2, NWGQ8		CSA 60950-1-07 2nd Ed IEC60384-14:2005 EN60384-14:2005 UL-60950-1, 2nd Ed	TÜV UL
1812	X7R	390pF 150pF to 4.7nF	(1,4)	Y2/X1 ⁽⁶⁾ NWGQ2, NWGQ8	CSA 60950-1-07 2nd Ed IEC60384-14:2005 EN60384-14:2005 UL-60950-1, 2nd Ed CSA 60950-1-07 2nd Ed	TÜV UL
2211	COG/NP0	4.7pF to 1nF	SP ⁽²⁾	Y2/X1 NWGQ2, NWGQ8	IEC60384-14:2005 EN60384-14:2005 	TÜV UL
2211	X7R	100pF to 3.9nF	SP ⁽²⁾	Y2/X1 NWGQ2, NWGQ8	IEC60384-14:2005 EN60384-14:2005 UL-60950-1, 2nd Ed CSA 60950-1-07 2nd Ed	TÜV UL
2215	COG/NP0	820pF to 1.0nF	SP ⁽²⁾	Y2/X1 NWGQ2, NWGQ8	IEC60384-14:2005 EN60384-14:2005 UL-60950-1, 2nd Ed CSA 60950-1-07 2nd Ed	TÜV UL
2215	X7R	2.7nF to 3.9nF	SP ⁽²⁾	Y2/X1 NWGQ2, NWGQ8	IEC60384-14:2005 EN60384-14:2005 UL-60950-1, 2nd Ed CSA 60950-1-07 2nd Ed	TÜV UL
2220	X7R	150pF to 5.6nF	B16	Y2/X1 ⁽²⁾ Y2/X1, ⁽¹⁾ FOWX2, FOWX8	IEC60384-14:2005 EN60384-14:2005 	TÜV UL
2220	X7R	150pF to 33nF	B17 ^(2,5)	X2	IEC60384-14:2005 EN60384:2005	TÜV

Termination availability

J & Y terminations only.

- J, Y, A & H terminations available.

- For cap values >1000pF available in "P" ProtectiCap™ termination only.

 For cap values >2200pF available in "P" ProtectiCap™ termination only.

 B17 values above 22nF available in "P" ProtectiCap™ termination only.

 The capacitors comply with the requirements of IEC/EN 60384-14:2005. For class Y2 or Y3 (as defined in the table) with the exception of insulation (creepage) distances.
- Unmarked capacitors also available as released in accordance with approval specifications. Family code SY2 applies. Unmarked capacitors also available as released in accordance with approval specifications. Family code SPU applies.

Ordering information - Safety Certified capacitors - Class SPU/SP ranges

18	808	J	A25	0102	J	С	Т	SP
	hip ize	Termination	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric codes	Packaging	Suffix code
22	808 2211 2215	J = Ni barrier Y = FlexiCap™ termination base with Ni barrier (100% matte tin plating). RoHS compliant. 2211/2215 only A = Silver base with Ni barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant. H = FlexiCap™ termination base with Ni barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant.	A25 = 250Vac	First digit is 0. Second and third digits are significant figures of capacitance code. The fourth digit is number of zeros following. Example: 0102 = 1.0nF	<10pF $B = \pm 0.10pF$ $C = \pm 0.25pF$ $D = \pm 0.50pF$ $\geq 10pF$ $F = \pm 1\%$ $G = \pm 2\%$ $J = \pm 5\%$ $K = \pm 10\%$ $M = \pm 20\%$	C = COG/NPO X = X7R	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays	SP = Surge Protection capacitors (marked and approved) SPU = Surge Protection capacitors (un-marked parts are in accordance with, but not certified)

Ordering information - Safety Certified capacitors - Class PY2/SY2

1808	J	A25	0102	J	X	Т	PY2
Chip size	Termination	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric codes	Packaging	Suffix code
1808 1812	J = Ni barrier Y = FlexiCap™ termination base with Ni barrier (100% matte tin plating). RoHS compliant. P = ProtectiCap™ FlexiCap™ termination base with Ni barrier, (100% matte tin plating).	A25 = 250Vac	First digit is 0. Second and third digits are significant figures of capacitance code. The fourth digit is number of zeros following. Example: 0102 = 1.0nF	<10pF $B = \pm 0.10pF$ $C = \pm 0.25pF$ $D = \pm 0.50pF$ $\geq 10pF$ $F = \pm 1\%$ $G = \pm 2\%$ $J = \pm 5\%$ $K = \pm 10\%$ $M = \pm 20\%$	C = COG/NPO X = X7R	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays	PY2 = Safety tested Surge Protection capacitors (marked and approved) SY2 = Surge Protection capacitors (un-marked parts are in accordance with, but not certified)


Ordering information - Safety Certified capacitors - Class B16/B17 ranges

2220	J	A25	0102	J	X	Т	B16
Chip size	Termination	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric codes	Packaging	Suffix code
2220	J = Ni barrier Y = FlexiCap™ termination base with Ni barrier (100% matte tin plating). RoHS compliant. A = Silver base with Ni barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant. H = FlexiCap™ termination base with Ni barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant. P = ProtectiCap™ FlexiCap™ termination base with Ni barrier, (100% matte tin plating).	A25 = 250Vac	First digit is 0. Second and third digits are significant figures of capacitance code. The fourth digit is number of zeros following. Example: 0102 = 1.0nF	$J = \pm 5\%$ $K = \pm 10\%$ $M = \pm 20\%$	X = X7R	T = 178mm (7") reel 1000 pieces R = 330mm (13") reel 4000 pieces B = Bulk pack - tubs or trays	B16 = Type A: X1/Y2 B17 = Type B: X2

Industry wide standard multilayer ceramic capacitors are supplied with a DC rating only. For AC use, Surge and Safety capacitors with an AC rating of 250Vac have been available but the capacitance range is limited as a result of the strict impulse and VP requirements in the international standards. Syfer Technology have developed a range which provides a solution for use at up to 250Vac 60Hz continuous use and provides for non safety-critical applications where extended capacitance ranges are required.

Capacitance range

Case sizes 0805 to 2220 are available in both X7R and COG/NPO dielectrics with capacitances of up to 120nF. The capacitance ranges are divided into four groups which are based on the voltage coefficient of capacitance, COG/NPO which has negligible capacitance shift with applied voltage and three subgroups of X7R. Type A with ±30% maximum capacitance shift 0V-240V, Type B with +30% to



-50% maximum capacitance shift 0V-240V and Type C with +30 to -80% maximum capacitance shift OV to

250Vac Non Safety Rated AC capacitors - minimum/maximum capacitance values

Chip size	0805	1206	1210	1808	1812	2220
COG/NP0	1.0pF - 470pF	1.0pF - 1.2nF	4.7pF - 2.2nF	4.7pF - 2.2nF	10pF - 5.6nF	10pF - 10nF
X7R A ‡30%	560pF - 1.5nF	1.5nF - 10nF	2.7nF - 22nF	2.7nF - 22nF	6.8nF - 56nF	12nF - 120nF
X7R B +30% -50%	1.8nF - 3.3nF	12nF	27nF	27nF	68nF - 82nF	-
X7R C +30% -80%	3.9nF - 10nF	15nF - 47nF	33nF - 100nF	33nF - 100nF	100nF - 120nF	-


Note: X7R A) has a VCC of ±30% over 0 to 240Vac 60Hz


X7R A) has a VCC of ±30% over 0 to 240Vac 60Hz
X7R B) has a VCC of ±30% to -50% over 0 to 240Vac 60Hz
X7R C) has a VCC of ±30% to -80% over 0 to 240Vac 60Hz

Measurement conditions described in Syfer Application Notes AN0033. Please see website for further details.

Ordering information - 250Vac Non Safety Rated AC capacitors

1812	Υ	A25	0103	K	X	Т
Chip size	Termination	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric codes	Packaging
0805 1206 1210 1808 1812 2220	Y = FlexiCap™ termination base with nickel barrier (100% matte tin plating). RoHS compliant. J = Silver base with nickel barrier (100% matte tin plating). RoHS compliant.	A25 = 250Vac 60Hz	<10pF Insert a P for the decimal point, eg P300 = 0.3pF, 8P20 = 8.2pF. ≥10pF 1st digit is 0. 2nd and 3rd digits are significant figures of capacitance code. The 4th digit is number of 0's following eg. 0103 = 10nF	<10pF $B = \pm 0.1pF$ $C = \pm 0.25pF$ $D = \pm 0.5pF$ $\geqslant 10pF$ $F = \pm 1\%$ $G = \pm 2\%$ $J = \pm 5\%$ $K = \pm 10\%$ $M = \pm 20\%$	C = COG/NPO X = X7R	T = 178mm (7*) reel R = 330mm (13*) reel B = Bulk pack - tubs or trays






115Vac 400Hz capacitors for aerospace applications

Syfer Technology has conducted reliability testing on standard surface mount ceramic capacitors in order to ensure their performance at 115Vac 400Hz and the associated voltage and frequency transients required by MIL-STD-704. Self heating will occur due to losses in the capacitor but has been measured at less than 25°C rise with neutral mounting conditions at room

Please note that the 115V 400Hz ranges are not RoHS 2011/65/EU compliant.



115Vac 400Hz capacitors - minimum/maximum capacitance values

	0805	1206	1210	1808	1812	2220		
Dielectric		Maximum capacitance values						
COG/NP0	1pF - 330pF	1pF - 1.5nF	3.9pF - 3.9nF	4.7pF - 3.9nF	10pF - 10nF	10pF - 15nF		
X7R	100pF - 4.7nF	100pF - 18nF	100pF - 39nF	100pF - 39nF	150pF - 82nF	220pF - 100nF		

Ordering information - 115Vac 400Hz capacitors

1206	Υ	A12	0103	J	X	Т
Chip size	Termination	Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric codes	Packaging
0805 1206 1210 1808 1812 2220	Y = FlexiCap™ termination base with nickel barrier (100% matte tin plating). RoHS compliant. H = FlexiCap™ termination base with nickel barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant. J = Silver base with nickel barrier (100% matte tin plating). RoHS compliant. A = Silver base with nickel barrier (Tin/lead plating with min. 10% lead). Not RoHS compliant.	A12 = 115Vac	First digit is 0. Second and third digits are significant figures of capacitance code. The fourth digit is number of zeros following. Example: 0103 = 10nF	$<4.7 pF \\ H = \pm 0.05 pF \\ B = \pm 0.10 pF \\ C = \pm 0.25 pF \\ D = \pm 0.50 pF \\ \geqslant 4.7 pF & <10 pF \\ C = \pm 0.10 pF \\ C = \pm 0.25 pF \\ D = \pm 0.50 pF \\ \geqslant 10 pF \\ F = \pm 1\% \\ G = \pm 2\% \\ J = \pm 5\% \\ K = \pm 10\% \\ M = \pm 20\%$	C = COG/NPO X = X7R	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays



High Dielectric Withstand Voltage capacitors (DWV range)

The Syfer DWV range is specifically designed for use in applications where a high Dielectric Withstand Voltage (DWV) is required.

These parts have a continuous rated voltage of 500Vdc minimum and are 100% DWV tested at the specified voltages to ensure Flashover (arcing) across the surface does not occur.

- High dielectric withstand voltages (DWV) of 1.5kV and 2.5kV
- These ratings are based on an application of the DWV voltage for a period of up to 60 seconds (where the charging current is limited to 50mA)
- Case sizes: 1206, 1210, 1808, 1812, 2220 and 2225
- COG/NPO and X7R dielectrics



- Capacitance values from 4.7pF to 120nF
- For full range information please see Syfer web site, or contact the sales office.

DWV capacitors - minimum/maximum capacitance range

		1206	1210	1808	1812	2220	2225
1 ELV	COG/NPO	4.7pF - 330pF	4.7pF - 1.0nF	4.7pF - 1.2nF	10pF - 2.2nF	100pF - 4.7nF	100pF - 5.6nF
1.5kV	X7R	4.7pF - 3.9nF	4.7pF - 10nF	4.7pF - 12nF	10pF - 33nF	100pF - 100nF	100pF - 120nF
2.5kV	COG/NP0	4.7pF - 220pF	4.7pF - 560nF	4.7pF - 1.0nF	10pF - 1.5nF	100pF - 3.3nF	100pF - 3.9nF
2.5KV	X7R	4.7pF - 1.0nF	4.7pF - 2.2nF	4.7pF - 2.7nF	10pF - 5.6nF	10pF - 15nF	100nF - 18nF

Ordering information - DWV capacitors

1812	J	1K5	0820	K	С	T	DWV
Chip size	Termination	Dielectric Withstand Voltage	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric codes	Packaging	Suffix code
1206 1210 1808 1812 2220 2225	Y = FlexiCap™ termination base with nickel barrier (100% matte tin plating). RoHS compliant. J = Silver base with nickel barrier (100% matte tin plating). RoHS compliant.	1K5 = 1.5kV 2K5 = 2.5kV	First digit is 0. Second and third digits are significant figures of capacitance code. The fourth digit is number of zeros following. Example: 0820 = 82pF	$<10pF$ B = ±0.10pF C = ±0.25pF D = ±0.50pF $\geqslant 10pF$ F = ±1% G = ±2% $\geqslant 10pF$ J = ±5% K = ±10% M = ±20%	C = COG/NPO X = X7R	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays	Dielectric Withstand Voltage



The X8R dielectric will operate from -55°C to +150°C, with a maximum capacitance change $\pm 15\%$ (without applied voltage).

The devices are available in sizes 0805 to 2225, with voltage ranges from 25V to 3kV and capacitance values from 270pF to 1.8 μ F.

The capacitors have been developed by Syfer to meet demand from various applications in the automotive and industrial markets and in other electronic equipment exposed to high temperatures. The increased use of electronics in automotive "under the hood" applications has created demand for this product range.

The X8R range incorporates a specially formulated termination with a nickel barrier finish that has been designed to enhance the mechanical performance of these SMD chip capacitors in harsh environments typically present in automotive applications.

For information, X8R dielectric contains lead within the ceramic and parts rated less than 250Vdc are not compliant with the EU 2011/65/EU RoHS directive.


Capacitance Range 270pF to 1.8µF

Temperature Coefficient of Capacitance (TCC)

 \pm 15% from -55°C to +150°C

Dissipation Factor (DF)

< 0.025



Insulation Resistance (IR) 100G Ω or 1000secs (whichever is the less). Dielectric Withstand Voltage (DWV) 2.5 x rated voltage for 5±1 seconds, 50mA charging current maximum. Ageing Rate 1% per decade (typical)

X8R High Temperature capacitors - minimum/maximum cap. values according to the rated d.c. voltage

		0805	1206	1210	1808	1812	2220	2225
Minimum capacita	ance value	680pF	270pF	680pF	390pF	1.0nF	2.7nF	3.9nF
	25V	56nF	180nF	330nF	470nF	680nF	1.5µF	1.8µF
	50V	33nF	120nF	220nF	270nF	470nF	680nF	1.0µF
	100V	15nF	56nF	120nF	150nF	220nF	470nF	560nF
	200/250V	10nF	33nF	68nF	82nF	120nF	220nF	330nF
	500V	3.9nF	18nF	39nF	47nF	100nF	180nF	270nF
Maximum capacitance value	630V	1.8nF	3.9nF	10nF	12nF	33nF	150nF	180nF
according to the rated dc voltage	1kV	1.0nF	2.2nF	4.7nF	5.6nF	18nF	39nF	56nF
rated dc voltage	1.2kV	-	1.8nF	3.9nF	4.7nF	12nF	33nF	39nF
	1.5kV	-	1.2nF	2.2nF	2.7nF	8.2nF	22nF	27nF
	2kV	-	470pF	1.2nF	1.8nF	4.7nF	12nF	18nF
	2.5kV	-	-	-	1.0nF	2.7nF	6.8nF	10nF
	3kV	-	-	-	680pF	2.2nF	4.7nF	5.6nF

Ordering information - X8R High Temperature capacitors

3	ruering information - Not riight remperature capacitors									
1206	Υ	100	0473	K	N	Т				
Chip size	Termination	Voltage d.c.	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric codes	Packaging				
0805 1206 1210 1808 1812 2220 2225	Y = FlexiCap [™] termination base with nickel barrier (100% matte tin plating). RoHS compliant.	025 = 25V 050 = 50V 100 = 100V 200 = 200V 250 = 250V 500 = 500V 630 = 630V 1K0 = 1kV 1K2 = 1.2kV 1K5 = 1.5kV 2K5 = 2.5kV 3K0 = 3kV	First digit is 0. Second and third digits are significant figures of capacitance code. The fourth digit is number of zeros following. Example: 0473 = 47000pF = 47nF	$J = \pm 5\%$ $K = \pm 10\%$ $M = \pm 20\%$	N = X8R	T = 178mm (7") reel R = 330mm (13") reel B = Bulk pack - tubs or trays				

The Syfer E01 and E07 ranges of feedthrough MLCC chip 'C' filters are 3 terminal chip devices designed to offer reduced inductance compared to conventional MLCCs when used in signal line filtering.


The filtered signal passes through the chip internal electrodes and the noise is filtered to the grounded side contacts, resulting in reduced length noise transmission paths.

Available in COG/NPO and X7R dielectrics, with current ratings of 300mA, 1A, 2A and voltage ratings of 25Vdc to 200Vdc. Also available with FlexiCap™ termination which is strongly recommended for new designs.

Commonly used in automotive applications, a range qualified to AECQ-200 is also available.




EO1 300mA, **EO7** 1A/2A





E01 / E07



1812

F 560nF-1.8µF

F 330nF-1.5µF

F 180nF-820nf

Dimensions

	0603	0805	1206	1806	
L	1.6 ± 0.2 (0.063 ± 0.008)	2.0 ± 0.3 (0.079 ± 0.012)	3.2 ± 0.3 (0.126 ± 0.012)	4.5 ± 0.35 (0.177 ± 0.014)	
W	0.8 ± 0.2 (0.003 ± 0.008)	1.25 ± 0.2 (0.049 ± 0.008)	1.6 ± 0.2 (0.063 ± 0.008)	1.6 ± 0.2 (0.063 ± 0.008)	
Т	0.5 ± 0.15 (0.02 ± 0.006)	1.0 ± 0.15 (0.039 ± 0.006)	1.1 ± 0.2 (0.043 ± 0.008)	1.1 ± 0.2 (0.043 ± 0.008)	
В1	0.3 ± 0.2 (0.012 ± 0.008)	0.60 ± 0.2 (0.024 ± 0.008)	0.95 ± 0.3 (0.037 ± 0.012)	1.4 ± 0.3 (0.055 ± 0.012)	
B2	0.2 ± 0.1 (0.008 ± 0.004)	0.3 ± 0.15 (0.012 ± 0.006)	0.5 ± 0.25 (0.02 ± 0.01)	0.5 ± 0.25 (0.02 ± 0.01)	

	0603	0805	1206	1806
Α	0.6 (0.024)	0.95 (0.037)	1.2 (0.047)	1.2 (0.047)
В	0.6 (0.024)	0.9 (0.035)	0.9 (0.035)	1.4 (0.055)
С	0.4 (0.016)	0.3 (0.012)	0.6 (0.024)	0.8 (0.031)
D	0.2 (0.008)	0.4 (0.016)	0.8 (0.031)	1.4 (0.055)
E	0.4 (0.016)	0.75 (0.030)	1.0 (0.039)	1.4 (0.055)

- Notes: 1) All dimensions mm (inches).
 2) Pad widths less than chip width gives improved mechanical performance.
 3) The solder stencil should place 4 discrete solder pads. The unprinted distance between ground pads is shown as dim E.
 4) Insulating the earth track underneath the filters is acceptable and can help avoid displacement of filter during soldering but can result in residue entrapment under the chip.


Тур	oe		EC)1		E07					
Chip	Size	0603	0805	1206	1806	0603	0805	1206	1806		
Max Current		300mA	300mA	300mA	300mA	1A	1A	2A	2A		
Rated Voltage	Dielectric		Minimum and maximum capacitance values								
25Vdc	COG/NP0	10pF-390pF	180pF-1.5nF	560pF-3.9nF	820pF-4.7nF	10pF-390pF	180pF-1.5nF	560pF-3.9nF	820pF-4.7nF		
25 Vac	X7R	2.7nF-18nF	470pF-100nF	5.6nF-330nF	3.9nF-560nF	2.7nF-18nF	820pF-100nF	10nF-330nF	22nF-560nF		
EOVdo	COG/NP0	10pF-56pF	22pF-820pF	22pF-3.3nF	22pF-3.9nF	12pF-56pF	10pF-220pF	22pF-1nF	100pF-1.5nf		
50Vdc	X7R	2.7nF-12nF	560pF-68nF	4.7nF-220nF	3.3nF-330nF	2.7nF-12nF	1nF-68nF	10nF-220nF	22nF-330nF		
1001/40	COG/NP0	-	22pF-560pF	22pF-2.2nF	22pF-3.3nF	-	10pF-120pF	22pF-560pF	100pF-680pl		
100Vdc	X7R	-	560pF-27nF	1.8nF-100nF	3.3nF-180nF	-	1nF-27nF	10nF-100nF	22nF-180nF		
	COC/NIDO			560nE 1 2nE	56nE 1nE			15nE 100nE	54nE 470nE		

Notes: 1) E01 ranges in red available as qualified AEC-Q200.
2) E07 25Vdc C0G/NP0 1206 and 1806 ranges in green, have maximum current of 1A.

Open board insertion loss performance in 50Ω system

Open Board Performance											
Capacitance	0.1MHz	1MHz	10MHz	100MHz	1GHz	Resonance Freq (MHz) approx.					
10pF	0	0	0	0	7.5	2200					
22pF	0	0	0	0	16	1600					
33pF	0	0	0	1	22	1350					
47pF	0	0	0	2	28	1150					
68pF	0	0	0	3	41	900					
100pF	0	0	0	5	28	800					
150pF	0	0	0	8	24	700					
220pF	0	0	0	12	20	600					
330pF	0	0	1	15	20	500					
470pF	0	0	2	18	20	425					
560pF	0	0	3	20	20	350					
680pF	0	0	4	22	20	300					
820pF	0	0	5	24	20	260					
1nF	0	0	7	27	20	220					
1.5nF	0	0	9	31	20	200					
2.2nF	0	0	12	34	20	170					
3.3nF	0	1	14	39	20	135					
4.7nF	0	2	18	46	20	110					
6.8nF	0	3	21	50	20	90					
10nF	0	5	24	48	20	80					
15nF	0	8	27	45	20	65					
22nF	0	12	31	43	20	56					
33nF	1	14	34	40	20	40					
47nF	2	17	38	40	20	34					
68nF	4	20	41	40	20	30					
100nF	6	24	45	40	20	28					
150nF	8	26	48	40	20	24					
220nF	10	30	52	40	20	17					
330nF	13	33	55	40	20	15.5					
470nF	16	36	60	40	20	14					
560nF	18	39	65	40	20	12					

E01 & E07 Insertion Loss



Ordering Information - E01 & E07 feedthrough capacitors

1206	Υ	100	0103	M	X	Т	E07
Chip Size	Termination	Voltage	Capacitance in picofarads (pF)	Tolerance	Dielectric	Packaging	Туре
0603 0805 1206 1806	J = Nickel Barrier (Tin) *Y = FlexiCap™ (Tin - X7R only) A = (Tin/Lead) Not RoHS compliant. *H = FlexiCap™ (Tin/Lead) Not RoHS compliant.	025 = 25V 050 = 50V 100 = 100V 200 = 200V	First digit is 0. Second and third digits are significant figures of capacitance code. The fourth digit is number of zeros following Example: 0103 = 10000pF.	M = ±20%	A = COG/NPO AEC-Q200 C = COG/NPO E = X7R AEC-Q200 X = X7R	T = 178mm (7") reel R = 330mm (13") reel B = Bulk	E01 E07

Note: *FlexiCap™ termination only available in X7R material. Please contact our Sales Office for any special requirements

Reeled quantities

178mm	0603	0805	1206	1806
(7") reel	4000	3000	2500	2500

330mm	0603	0805	1206	1806	
(13") reel	16000	12000	10000	10000	

X2Y

The Syfer X2Y Integrated Passive Component is a 3 terminal EMI chip device.

When used in balanced line applications, the revolutionary design provides simultaneous line-to-line and line-to-ground filtering, using a single ceramic chip. In this way, differential and common mode filtering are provided in one device.

For unbalanced applications, it provides ultra low ESL (equivalent series inductance). Capable of replacing 2 or more conventional devices, it is ideal for balanced and unbalanced lines, twisted pairs and dc motors, in automotive, audio, sensor and other applications.

Available in sizes from 0603 to 2220, these filters can prove invaluable in meeting stringent EMC demands.

Manufactured in the UK by Syfer Technology Limited under licence from X2Y Attenuators LLC.

Dielectric X7R or COG/NPO

At 1000hr point

Electrical configuration

Multiple capacitance

Capacitance measurement

Typical capacitance matching Better than 5% (down to 1% available on request) Temperature rating

-55°C to 125°C

Insulation resistance


100Gohms or 1000s (whichever is the less)



Dielectric withstand voltage ≤200V 2.5 times rated Volts for 5 secs 500V 1.5 times rated Volts for 5 secs Charging current limited to 50mA Max.

Ty	yp e	E03								
Chip size		0603	0805	1206	1410	1812	2220			
Rated voltage	Dielectric	Minimum and maximum capaci			um capacitance v	alues				
16Vdc	COG/NPO	150pF	-	-	-	-	-			
TOVUC	X7R	15nF	-	-	-	-	-			
25Vdc	COG/NP0	120pF	560pF - 820pF	1.8nF - 3.3nF	6.8nF - 8.2nF	12nF - 15nF	22nF - 33nF			
	X7R	12nF	56nF - 68nF	-	470nF	820nF	1.2µF			
50Vdc	COG/NP0	10pF - 100pF	390pF - 470pF	1.2nF - 1.5nF	4.7nF - 5.6nF	8.2nF - 10nF	18nF			
SOVAC	X7R	150pF - 10nF	18nF - 47nF	56nF - 220nF	180nF - 400nF	390nF - 680nF	560nF - 1.0μF			
100Vdc	COG/NP0	-	10pF - 330pF	22pF - 1.0nF	100pF - 3.9nF	820pF - 6.8nF	1.0nF - 15nF			
TOOVAC	X7R	-	470pF - 15nF	1.5nF - 47nF	4.7nF - 150nF	8.2nF - 330nF	10nF - 470nF			
200Vdc	COG/NP0	-	-	22pF - 1.0nF	100pF - 3.3nF	820pF - 5.6nF	1.0nF - 15nF			
200 vac	X7R	-	-	820pF - 33nF	1.2nF - 120nF	2.7nF - 180nF	4.7nF - 470nF			
500Vdc	COG/NP0	-	-	-	-	820pF - 3.9nF	1.0nF - 10nF			
SOUVAC	X7R	-	-	-	-	2.7nF - 100nF	4.7nF - 180nF			

Notes: 1) For some lower capacitance parts, higher voltage rated parts may be supplied.



	0603	0805	1206	1410	1812	2220
L	1.6±0.2 (0.063±0.008)	2.0±0.3 (0.08±0.012)	3.2±0.3 (0.126±0.012)	3.6±0.3 (0.14±0.012)	4.5±0.35 (0.18±0.014)	5.7±0.4 (0.22±0.016)
W	0.8±0.2 (0.03±0.008)	±0.008) (0.05±0.008) (0.063		2.5±0.3 (0.1±0.012)	3.2±0.3 (0.126±0.012)	5.0±0.4 (0.2±0.016)
т	0.5±0.15 (0.02±0.006)	1.0±0.15 (0.04±0.006)	1.1±0.2 (0.043±0.008)	2.0 max. (0.08 max.)	2.1 max. (0.08 max.)	2.5 max. (0.1 max.)
B1	0.4±0.15 (0.016±0.006)	0.5±0.25 (0.02±0.01)	0.95±0.3 (0.037±0.012)	1.20±0.3 (0.047±0.012)	1.4±0.35 (0.06±0.014)	2.25±0.4 (0.09±0.016)
B2	0.25±0.15 (0.010±0.006)	0.3±0.15 (0.012±0.006)	0.5±0.25 (0.02±0.01)	0.5±0.25 (0.02±0.01)	0.75±0.25 (0.03±0.01)	0.75±0.25 (0.03±0.01)

Notes: 1) All dimensions mm (inches).

- Pad widths less than chip width gives improved mechanical performance.
 The solder stencil should place 4 discrete solder pads. The un-printed distance between ground pads
- is shown as dim E.
- is snown as un e. 4) Insulating the earth track underneath the filters is acceptable and can help avoid displacement of filter during soldering but can result in residue entrapment under the chip.

D	<u> </u>
-B-	ľ.
	EA
	-C

Recommended solder lands


	0603	0805	1206	1410	1812	2220
Α	0.6 (0.024)	0.95 (0.037)	1.2 (0.047)	2.05 (0.08)	2.65 (0.104)	4.15 (0.163)
В	0.6 (0.024)	0.9 (0.035)	0.9 (0.035)	1.0 (0.040)	1.4 (0.055)	1.4 (0.055)
С	0.4 (0.016)	0.3 (0.012)	0.6 (0.024)	0.7 (0.028)	0.8 (0.031)	1.2 (0.047)
D	0.2 (0.008)	0.4 (0.016)	0.8 (0.031)	0.9 (0.035)	1.4 (0.055)	1.8 (0.071)
Ε	0.4 (0.016)	0.75 (0.030)	1.0 (0.039)	1.85 (0.071)	2.05 (0.080)	3.95 (0.156)


AEC-Q200 range (E03) - capacitance values

X2Y Integrated Passive Components

Chip siz	Chip size		0805 1206		1812
E0Vdo	COG/NP0	390pF - 470pF	1.2nF - 1.5nF	4.7nF - 5.6nF	8.2nF - 10nF
50Vdc	X7R	18nF - 33nF	56nF - 150nF	180nF - 330nF	390nF- 560nF
100Vdo	COG/NP0	10pF - 330pF	22pF - 1.0nF	100pF - 3.9nF	820pF - 6.8nF
100Vdc	X7R	470pF - 15nF	1.5nF - 47nF	4.7nF - 150nF	8.2nF - 330nF

Component	Advantages	Disadvantages	Applications
Chip capacitor	Industry standard	Requires 1 per line High inductance Capacitance matching problems	By-pass Low frequency
3 terminal feedthrough	Feedthrough Lower inductance	Current limited	Feedthrough Unbalanced lines High frequency
Syfer X2Y Integrated Passive Component	Very low inductance Replaces 2 (or 3) components Negates the effects of temperature, voltage and ageing Provides both common mode and differential mode attenuation Can be used on balanced & unbalanced lines	Care must be taken to optimise circuit design	By-pass Balanced lines High frequency dc electric motors Unbalanced lines Audio amplifiers CANBUS





Ordering information

0. 40	giinoimation						
1812	Υ	100	0334	M	X	T	E03
Chip Size	Termination	Voltage	Capacitance in picofarads (pF) C ₁	Tolerance	Dielectric	Packaging	Туре
0603 0805 1206 1410 1812 2220	J = Nickel Barrier (Tin) *Y = FlexiCap™ (Tin - X7R only) A = (Tin/Lead) Not RoHS compliant. *H = FlexiCap™ (Tin/Lead) Not RoHS compliant.	016 = 16V 025 = 25V 050 = 50V 100 = 100V 200 = 200V 500 = 500V	First digit is 0. Second and third digits are significant figures of capacitance code. The fourth digit is number of zeros following Example: 0334=330nF. Note: C ₁ = 2C ₂	M = ±20% (Tighter tolerances may be available on request).	A = COG/NPO AEC-Q200 C = COG/NPO E = X7R AEC-Q200 X = X7R	T = 178mm (7") reel R = 330mm (13") reel B = Bulk	Syfer X2Y Integrated Passive Component

 $Note: {}^{\star}\mathsf{FlexiCap^{\intercal M}} \ termination \ only \ available \ in \ \mathsf{X7R} \ material. \ Please \ contact \ the \ sales \ office \ for \ any \ special \ requirements.$


Reeled quantities

178mm	0603	0805	1206	1410	1812	2220
(7") reel	4000	3000	2500	2000	1000	1000

330mm	0603	0805	1206	1410	1812	2220	
(13") reel	16000	12000	10000	8000	4000	4000	

43


Tape and reel packing of surface mounting chip capacitors for automatic placement are in accordance with IEC60286-3.



Peel force


The peel force of the top sealing tape is between 0.2 and 1.0 Newton at 180°. The breaking force of the carrier and sealing tape in the direction of unreeling is greater than 10 Newtons.

Reel dimensions mm (inches)



Symbol	Description	178mm reel	330mm reel
Α	Reel diameter	178 (7)	330 (13)
G	Reel inside width	8.4 (0.33)	12.4 (0.49)
Т	Reel outside width	14.4 (0.56) max	18.4 (0.72) max

Tape dimensions



		Dimensions mm (inches)				
Symbol	Description	8mm tape	12mm tape			
$\begin{array}{c} A_{_{0}} \\ B_{_{0}} \\ K_{_{0}} \end{array}$	Width of cavity Length of cavity Depth of cavity	Dependent on chip siz	e to minimize rotation			
W	Width of tape	8.0 (0.315)	12.0 (0.472)			
F	Distance between drive hole centres and cavity centres	3.5 (0.138)	5.5 (0.213)			
Е	Distance between drive hole centres and tape edge	1.75 (0.069)				
P ₁	Distance between cavity centres	4.0 (0.156)	8.0 (0.315)			
P ₂	Axial distance between drive hole centres and cavity centres	2.0 (0	.079)			
P _o	Axial distance between drive hole centres	4.0 (0	.156)			
D _o	Drive hole diameter	1.5 (0	.059)			
D ₁	Diameter of cavity piercing	1.0 (0.039)	1.5 (0.059)			
Т	Carrier tape thickness	0.3 (0.012) ±0.1 (0.004)	0.4 (0.016) ±0.1 (0.004)			
t ₁	Top tape thickness	0.1 (0.00	04) max			

Missing components


Packaging information

The number of missing components in the tape may not exceed 0.25% of the total quantity with not more than three consecutive components missing. This must be followed by at least six properly placed components.

Identification

Each reel is labelled with the following information: manufacturer, chip size, capacitance, tolerance, rated voltage, dielectric type, batch number, date code and quantity of components.

Leader and Trailer



Component orientation

Tape and reeling is in accordance with IEC 60286 part 3, which defines the packaging specifications of leadless components on continuous tapes.


Notes: 1) IEC60286-3 states Ao_< Bo (see Tape dimensions on page 44).

 Regarding the orientation of 1825 and 2225 components, the termination bands are right to left, NOT front to back. Please see diagram.


Outer Packaging

Outer carton dimensions mm (inches) max.

Reel Size	No. of reels L		W	Т
178 (7.0)	1	185 (7.28)	185 (7.28)	25 (0.98)
178 (7.0)	4	190 (7.48)	195 (7.76)	75 (2.95)
330 (13.0)	1	335 (13.19)	335 (13.19)	25 (0.98)



Orientation of 1825 & 2225 components



Reel quantities

Chip size		0402	0505	0603	0805	1111	1206	1210	1410	1808	1812	1825	2211	2215	2220	2225
Max. chip thickness		0.5mm	1.3mm	0.8mm	1.3mm	2.0mm	1.6mm	2.0mm	2.0mm	2.0mm	2.5mm	2.5mm	2.5mm	2.5mm	2.5mm	2.5mm
		0.02"	0.05"	0.03"	0.05"	0.08"	0.06"	0.08"	0.08"	0.08"	0.1"	0.1"	0.1"	0.1"	0.1"	0.1"
Reel quantities	178mm (7")	5000	2500	4000	3000	1000	2500	2000	2000	1500	500/ 1000	500	750	500	500/ 1000	500/ 1000
	330mm (13")	-	-	16000	12000	-	10000	8000	8000	6000	2000/ 4000	2000	-	4000	2000/ 4000	2000/ 4000

Notes:

1) The above quantities per reel are for the maximum manufactured chip thickness. Thinner chips can be taped in larger quantities per reel.


2) Where two different quantities are shown for the same case size, please contact the Sales Office to determine the exact quantity for any specific part number.

Bulk packing - tubs

Chips are supplied in rigid re-sealable plastic tubs together with impact cushioning wadding. Tubs are labelled with the details: chip size, capacitance, tolerance, rated voltage, dielectric type, batch number, date code and quantity of components.

Dimensions mm (inches)

Н	60 (2.36)
D	50 (1.97)



Syfer Technology produces a wide range of dipped radial leaded capacitors. These are available in rated voltages of 50V up to 6kV. Although our catalogue range extends to 6kV, we are able to offer a capability for specials up to 12kV. Our larger case sizes and high voltage versions are particularly in demand, especially for mil/aero and medical power supply applications. Please contact our Sales Office to discuss any special requirements.

- High working voltage up to 12kVdc
- Large case sizes
- RoHS compliant versions
- Tin-lead plated wire option to reduce tin whiskers (quote suffix A97 for 8111 to 8141 & A31 for 8151, 8161, 8171).



		8111M	8111N	8121M	8121N	8121T	8131M	8131M T =	8131T	8141M	8151M	8151M T =	8161M	8161M T =	8171M	8171M T =
								6.3mm				6.3mm		7.0mm		7.0mm
Min. cap	COG/NPO	4.7pF	4.7pF	4.7pF	4.7pF	4.7pF	4.7pF	-	10pF	4.7pF	10pF	-	27pF	-	47pF	-
values	X7R	100pF	100pF	100pF	100pF	330pF	100pF	-	150pF	100pF	470pF		1.0nF		1.8nF	
50/63V	COG/NPO	5.6nF	5.6nF	33nF	33nF	33nF	220nF	-	100nF	220nF	330nF	-	680nF	-	1.0µF	-
307034	X7R	220nF	220nF	1.0µF	1.0µF	1.0µF	3.3µF		2.2µF	4.7µF	10µF	-	15µF	-	22µF	-
100V	COG/NPO	2.2nF	2.2nF	18nF	18nF	18nF	82nF	-	47nF	82nF	270nF	-	470nF	-	680nF	-
1004	X7R	100nF	100nF	680nF	680nF	680nF	2.7µF		1.5µF	2.7µF	5.6µF		10µF	-	15µF	-
200/	COG/NPO	1.0nF	1.0nF	8.2nF	8.2nF	8.2nF	47nF	68nF	22nF	47nF	120nF	180nF	270nF	330nF	390nF	560nF
250V	X7R	56nF	56nF	330nF	330nF	330nF	1.5µF	-	680nF	1.5µF	3.3µF	-	5.6µF	-	10μF	-
500V	COG/NPO	680pF	680pF	6.8nF	6.8nF	6.8nF	33nF	47nF	15nF	33nF	82nF	120nF	180nF	270nF	270nF	470nF
500V	X7R	15nF	15nF	150nF	150nF	150nF	820nF	-	330nF	820nF	1.0µF	-	1.8µF	-	3.3µF	-
(20)/	COG/NPO	560pF	560pF	3.9nF	3.9nF	3.9nF	22nF	39nF	10nF	22nF	68nF	100nF	120nF	180nF	220nF	390nF
630V	X7R	12nF	12nF	100nF	100nF	100nF	390nF	-	180nF	470nF	680nF		1.2µF	-	2.2µF	-
1kV	COG/NPO	180pF	180pF	2.2nF	2.2nF	2.2nF	18nF	27nF	6.8nF	18nF	47nF	82nF	82nF	150nF	150nF	270nF
IKV	X7R	10nF	10nF	47nF	47nF	47nF	150nF		100nF	150nF	180nF		390nF		1.0µF	
4.0114	COG/NPO	120pF	120pF	1.5nF	1.5nF	1.5nF	12nF	22nF	4.7nF	12nF	33nF	56nF	68nF	100nF	100nF	180nF
1.2kV	X7R	-	-	10nF	10nF	10nF	100nF	-	33nF	100nF	150nF		220nF	-	470nF	
	COG/NPO	82pF	82pF	820pF	820pF	820pF	6.8nF	12nF	2.7nF	6.8nF	22nF	39nF	39nF	68nF	68nF	120nF
1.5kV	X7R	-	-	6.8nF	6.8nF	6.8nF	68nF	-	22nF	68nF	100nF		150nF	-	330nF	-
	COG/NPO	39pF	39pF	390pF	390pF	390pF	4.7nF	6.8nF	1.5nF	4.7nF	10nF	18nF	22nF	39nF	39nF	68nF
2kV	X7R			4.7nF	4.7nF	4.7nF	33nF		10nF	47nF	47nF		82nF		150nF	
	COG/NPO	-	-	220pF	220pF	220pF	2.2nF	3.9nF	820pF	2.2nF	6.8nF	12nF	12nF	22nF	22nF	39nF
2.5kV	X7R			-		-	12nF		3.3nF	12nF	33nF		68nF		100nF	
	COG/NPO	-	-	150pF	150pF	150pF	1.8nF	2.7nF	560pF	1.8nF	4.7nF	8.2nF	10nF	18nF	15nF	27nF
3kV	X7R			-	-	-	8.2nF		2.7nF	10nF	22nF		47nF		82nF	
	COG/NPO	-	-	-	-	-	820pF	1.5nF	270pF	820pF	1.8nF	3.3nF	4.7nF	6.8nF	8.2nF	15nF
4kV	X7R		-	-	-	-	5.6nF		2.2nF	5.6nF	6.8nF		15nF	-	33nF	-
	COG/NPO	-	-	. ,	· \	-	560pF	1.0nF	180pF	560pF	1.5nF	2.2nF	2.7nF	4.7nF	5.6nF	10nF
5kV	X7R	-	-	5		-	4.7nF		1.2nF	4.7nF	5.6nF	-	10nF	-	22nF	
	COG/NPO	-	-//	-	2	-	390pF	680pF	120pF	390pF	1.0nF	1.5nF	1.8nF	3.3nF	3.9nF	6.8nF
6kV	X7R	- /				-	2.7nF		1.0nF	2.7nF	4.7nF		8.2nF		15nF	
	COG/NPO	-	- //		-/	-	-	-	-	-	150pF	-	330pF	-	680pF	-
8kV	X7R		-	- /		-	-	-	-	-	1.5nF		4.7nF		6.8nF	-
	COG/NPO		-		-58		-	-		-	100pF		180pF		470pF	-
10kV	X7R					-				-	1.0nF		2.2nF		4.7nF	
	COG/NPO	-	-			-		-	-	-	68pF		120pF		220pF	-
12kV	X7R			-	-	-				-	820pF		1.2nF		2.2nF	-
		8111M	8111N	8121M	8121N	8121T	8131M	8131M T =	8131T	8141M	8151M	8151M T =	8161M	8161M T =	8171M	8171M T =

Note: T = Maximum thickness.

46

Dimensions - Radial Leaded capacitors


	Width		Height	Thickness	Lead Space	Lead Diameter
	Pattern	(X) max. mm (inches)	(Y) max. mm (inches)	(Z) max. mm (inches)	(S) mm (inches)	(d) mm (inches)
8111M	Α	3.81 (0.15)	5.31 (0.21)	2.54 (0.10)	2.54 ±0.4 (0.1 ±0.016)	0.5 ±0.05 (0.02 ±0.002)
8111N	В	3.81 (0.15)	5.31 (0.21)	2.54 (0.10)	5.08 ±0.4 (0.2 ±0.016)	0.5 ±0.05 (0.02 ±0.002)
8121M	Α	5.08 (0.20)	6.58 (0.26)	3.18 (0.125)	2.54 ±0.4 (0.1 ±0.016)	0.5 ±0.05 (0.02 ±0.002)
8121N	В	5.08 (0.20)	6.58 (0.26)	3.18 (0.125)	5.08 ±0.4 (0.2 ±0.016)	0.5 ±0.05 (0.02 ±0.002)
8121T	В	10.16 (0.40)	5.80 (0.23)	4.50 (0.18)	7.62 ±0.4 (0.30 ±0.016)	0.5 ±0.05 (0.02 ±0.002)
8131M	Α	7.62 (0.30)	9.12 (0.36)	3.81/6.30 (0.15/0.25)	5.08 ±0.4 (0.2 ±0.016)	0.5 ±0.05 (0.02 ±0.002)
8131T	В	10.16 (0.40)	9.12 (0.36)	4.50 (0.18)	7.62 ±0.4 (0.30 ±0.016)	0.5 ±0.05 (0.02 ±0.002)
8141M	Α	10.16 (0.40)	11.66 (0.46)	3.81 (0.15)	5.08 ±0.4 (0.2 ±0.016)	0.5 ±0.05 (0.02 ±0.002)
8151M	А	12.70 (0.50)	14.20 (0.56)	5.08/6.30 (0.20/0.25)	10.1 ±0.4 (0.4 ±0.016)	0.6 ±0.05 (0.025 ±0.002)
8161M	А	18.50 (0.73)	16.50 (0.65)	6.00/7.00 (0.24/0.28)	14.5 ±0.5 (0.57 ±0.02)	0.6 ±0.05 (0.025 ±0.002)
8165M	Α	19.00 (0.75)	19.00 (0.75)	4.25 (0.17)	17.5 ±0.5 (0.67 ±0.02)	0.6 ±0.05 (0.025 ±0.002)
8171M	Α	25.00 (0.98)	20.00 (0.79)	6.00/7.00 (0.24/0.28)	20.5 ±0.5 (0.81 ±0.02)	0.6 ±0.05 (0.025 ±0.002)

Pattern A

Marking information

All encapsulated capacitors are marked with:- Capacitance value, tolerance, rated d.c. voltage, dielectric, and where size permits the Syfer Technology 'S' logo.

Example: 1000pF ±10% 50V 2X1 dielectric



X - - - Z - X - - - Z Y Seating Plane Plane

Pattern B

Note: Pattern A may be substituted with Pattern B at Syfer's discretion.

Ordering information - Radial Leaded capacitors

8111M	100	100 0102 J		С				
Type No./ Size ref	Voltage d.c. (marking code)	Capacitance in picofarads (pF)	Capacitance tolerance	Dielectric Rel Release codes	Suffix code	Suffix code		
8111M 8111N 8121M 8121N 8121T 8131M 8131T 8141M 8151M 8161M 8165M 8171M	050 = 50V (C) 063 = 63V (D) 100 = 100V (E) 200 = 200V (F) 250 = 250V 500 = 500V (Q) 630 = 630V 1K0 = 1KV 1K2 = 1.2kV 1K5 = 1.5kV 2K0 = 2kV 2K5 = 2.5kV 3K0 = 3kV 4K0 = 4kV 5K0 = 5kV	<10pF Insert a P for the decimal point as the second character. eg. 8P20 = 8.2pF ≥10pF First digit is 0. Second and third digits are significant figures of capacitance code. Fourth digit is number of zeros eg. 0101 = 100pF	<10pF D: ± 0.5pF F: ± 1.0pF ≥10pF J: ± 5% K: ± 10% M: ± 20% ≥27pF G: ± 2% (COG/NPO only).	C = COG/NPO (1B/CG; CG/BP) X = X7R (2R1) To Special Order B = 2X1 (BX) R = 2C1 (BZ)	Used for specific customer requirements.	C42 denotes RoHS compliant. A31 or A97 denote non-RoHS tin/lead wires. Suffix A97 for 8111 to 8141 & A31 for 8151, 8161, 8171.		
	6K0 = 6kV 8K0 = 8kV 10K = 10kV 12K = 12kV		Notes: The voltage code may be replaced with the complete voltage (e.g. 1500V = 1K5V) at Syfer's discretion. Marking may be over both sides of the component as necessary.					


Radial Leaded capacitors COG/NP0 & X7R ranges 8111M / 8111N 8121M / 8121N 8121T 8131M 8131T X7R COG/NPO COG/NPO COG/NPO COG/NPO COG/NPO X7R X7R X7R X7R 4.7pF 4p7 5.6 5p6 6.8 6p8 8.2 8p2 4.7pF 4p7 10pF 100 12 120 10pF 100 12 120 15 150 15 150 18 180 18 180 22 22 220 220 27 270 33 330 27 270 33 330 39 390 47 470 39 390 47 470 56 560 68 680 82 820 56 560 68 680 82 820 100pF 101 100pF 101 120 121 120 121 150 151 150 151 180 181 181 180 220 221 270 271 220 221 270 271 330 331 330 331 390 391 390 391 470 471 560 561 560 561 680 681 820 821 820 821 1.0nF 102 1.0nF 102 1.2 122 122 1.5 152 1.5 152 1.8 182 1.8 182 2.2 222 2.2 222 2.7 272 272 2.7 3.3 332 3.3 332 3.9 392 4.7 472 5.6 562 6.8 682 8.2 822 10nF 103 12 123 3.9 392 4.7 472 5.6 562 6.8 682 8.2 822 10nF 103 12 123 15 153 18 183 15 153 183 18 22 223 27 273 22 223 27 273 33 333 33 333 39 393 39 393 47 473 47 473 56 563 563 68 683 68 683 82 823 82 823 100nF 104 100nF 104 120 124 150 154 150 154 180 184 180 184 220 224 220 224 270 274 270 274 330 334 330 334 390 394 390 394 470 474 470 474 560 564 680 684 820 824 560 564 680 684 820 824 820 824 1.0μF 105 1.2 125 1.5 155 1.8 185 1.0µF 105 1.0µF 105 1.2 125 1.5 155 1.8 185 2.2 225 2.7 275 3.3 335 2.2 225 2.7 275 3.3 335 3.9 395 4.7 475 3.9 395 4.7 475 5.6 565 5.6 565 6.8 685 6.8 685 8.2 825 8.2 825 10μF 106 10μF 106 126 12 126 15µF 156

ALX C

MEXC

48

Radial Leaded capacitors COG/NPO & X7R ranges



18x6

51

MEXC

50

Cropped leads

Cropped leads between 4.0 (0.157) and 30.0 (1.18) are available to special order. Some of the preferred codes are listed below, together with the appropriate suffix code. Dimensions as for standard product except as specified.

All radial ranges
Lead length (L) 6 ±1 (0.236 ±0.04)
from seating plane

Suffix code - AE4 All radial ranges
Lead length (L) 4 ± 1 (0.162 ± 0.04) from seating plane

Suffix code - AD7 All radial ranges

 $5 \pm 1 (0.2 \pm 0.04)$

from seating plane

Suffix code - AD5 All radial ranges $10 \pm 1 (0.4 \pm 0.04)$ from seating plane

Dimensions mm (inches)

Snap in leads

Various forms of snap in leads (preformed) are available to special order, some of the preferred suffix codes are listed below. Dimensions as for standard product except as specified.

Suffix code - AD1

For PCB holes 0.9mm diameter Types 8121N and 8131M

Y = 8121N 8 (0.315) Max 8131M 10 (0.394) Max

L = Min: 2.75 (0.108)Max: 3.50 (0.138)


Suffix code - AD3

For PCB holes 1.2mm diameter Types 8121N

Dimensions

Y = 8 (0.315) Max

L = Min: 2.75 (0.108)Max: 3.50 (0.138)



6.6±0.5


Suffix code - AD2

For PCB holes 1.2mm diameter Types 8131M

Dimensions

Y = 10 (0.294) Max

L = Min: 2.75 (0.108) Max: 3.50 (0.138)




Bandoliered suffix codes

Dipped radial leaded with 2.54 and 5.08mm lead spacing can be supplied bandoliered on reels or in ammo boxes to special order. Some of the preferred suffix codes for bandoliered products are given below.

For bandoliered products the minimum order quantity, pieces, is specified in the tables below, larger orders must be in multiples of this quantity.

Suffix code


Dipped – straight and formed leads



					Reel	AMMC) pack
Product code	Lead style	Diagram	Н	H _o	2500pcs	1000pcs	2000pcs
8111M	Straight 2.54 crs	Α	19±1	-	C01	C02	C11
8111M	Straight 2.54 crs	Α	16±0.5	-	C30	C31	C32
8111N	Formed 5.08 crs	В	-	16±0.5	C01	C02	C11
8121M	Straight 2.54 crs	Α	19±1	-	C01	C02	C11
8121M	Straight 2.54 crs	А	16±0.5	-	C30	C31	C32
8121N	Formed 5.08 crs	В	-	16±0.5	C01	C02	C11
8131M	Straight 5.08 crs	А	19±1	-	C01	C02	C11
8131M	Straight 5.08 crs	А	16±0.5	-	C30	C31	C32

8121T and 8131T available in bulk packaging only.

Dipped - stand-off lead form



52

This style has been developed to provide a meniscus-free seating plane with a stress relieving form for auto-insertion.

Product code	Lead style	Y max	H _o	2500pcs	1000pcs	2000pcs
8111N	Formed 5.08 crs	7.5	16±0.5	C12	C23	C22
8111N	Formed 5.08 crs	7.5	19±1	C13	C25	C24
8121N	Formed 5.08 crs	8.5	16±0.5	C12	C23	C22
8121N	Formed 5.08 crs	8.5	19±1	C13	C25	C24


A maximum of 3 consecutive components may be missing from the bandolier, followed by at least 6 filled positions. Components missing from the bandolier are included in the total quantity, whereby the number of missing components may not exceed 0.25% of this total per packing module. At the beginning and end of a reel the bandolier will exhibit at least 10 blank positions.

Minimum pull strength of product from tape = 5N.

Packaging information

Each reel/carton is provided with a label showing the: Manufacturer, product style, batch identification, quantity and date code.

Labelling with bar codes (code 39) is available on request.




In accordance with IEC 60286 part 2.

Dimensions mm (inches)


Description	Symbol	2.5mm lead space	5mm lead space	Tolerance
Lead wire diameter	d	0.5 (0.02) 0.6 (0.025)	0.5 (0.02) 0.6 (0.025)	±0.05 (0.002)
Component pitch	Р	12.7 (0.5)	12.7 (0.5)	1.00 (0.04)
Feed hole pitch	P _o	12.7 (0.5)	12.7 (0.5)	±0.30 (0.01)
Feed hole centre to lead	P ₁	5.08 (0.2)	3.81 (0.15)	±0.70 (0.03)
Feed hole centre to component	P ₂	6.35 (0.25)	6.35 (0.25)	±0.70 (0.03)
Lead spacing	F	2.54 (0.10)	5.08 (0.20)	+0.6 (0.02) -0.1 (0.004)
Component alignment	Δh	0	0	±2.00(0.08)
Tape width	W	18.0 (0.70)	18.0 (0.70)	+1.00 (0.04) -0.50 (0.02)
Hold down tape width	W _o	6.0 (0.23)	6.0 (0.23)	±0.30 (0.01)
Hole position	W ₁	9.0 (0.35)	9.0 (0.35)	±0.50 (0.02)
Hold down tape position	W_{2}	0.50 (0.02)	0.50 (0.02)	Max
Height to seating plane from tape centre (straight leads) (2)	Н	16 (0.63) to 20 (0.79)	16 (0.63) to 20 (0.79)	As required
Height to seating plane from tape centre (formed leads) (2)	H _o	16 (0.63) to 20 (0.79)	16 (0.63) to 20 (0.79)	As required
Height to top of component from tape centre	H ₁	32.2 (1.26)	32.2 (1.26)	Max
Feed hole diameter	D _o	4.0 (0.16)	4.0 (0.16)	±0.20 (0.008)
Carrier tape plus adhesive tape thickness	t	0.7 (0.03)	0.7 (0.03)	±0.20 (0.008)
Carrier tape thickness	-	0.5 (0.02)	0.5 (0.02)	±0.10 (0.004)
Cut out component snipped lead length from tape centre	L	11.0 (0.43)	11.0 (0.43)	Max
Lead wire protusion from hold down	L ₂	2.0 (0.08)	2.0 (0.08)	Max

Bandoliered reels



The adhesive tape faces outwards. The dispensing direction is as shown. For the protection of the components a paper inlay is inserted between the windings of the bandolier. At the end of the bandolier this paper inlay continues for at least a further two rotations.

Bandoliered ammo packing



ACXC

BSC Filters Limited

Dover House, 10-11 Stirling Park, Bleriot Way, Clifton Moor, York, YO30 4WU UK

> Phone: +44 1904 694250 Fax: +44 1904 694260 Email: sales@bscfilters.com

Dielectric Laboratories, Inc

2777 Route 20 East, Cazenovia, NY 13035 USA

Phone: +1 315 655 8710 Fax: +1 315 655 0445 Email: sales@dilabs.com

Dow-Key Microwave

4822 McGrath Street, Ventura, CA 93003 USA

Phone: +1 805 650 0260 Fax: +1 805 650 1734 Email: askdk@dowkey.com

K&L Microwave

2250 Northwood Drive, Salisbury, MD 21801 USA

Phone: +1 410 749 2424 Fax: +1 443 260 2268 Email: sales@klmicrowave.com

Novacap

25111 Anza Drive, Valencia, CA 91355 USA

Phone: +1 661 295 5920 Fax: +1 661 295 5928 Email: info@novacap.com

Pole/Zero Corporation

5558 Union Centre Drive, West Chester, OH 45069 USA

Phone: +1 513 870 9060 Fax: +1 513 870 9064 Email: support@polezero.com

Syfer Technology Limited

Old Stoke Road, Arminghall, Norwich, NR14 8SQ UK

Phone: +44 1603 723300 Fax: +44 1603 723301 Email: sales@syfer.co.uk

Voltronics Corporation

2250 Northwood Drive, Salisbury, MD 21801 USA

Phone: +1 410 749 2424 Fax: +1 443 260 2263 Email: info@voltronicscorp.com



















Ceramic & Microwave Products (CMP) designs, manufactures and sells special electronic components and systems, including high-performance filters, switches, capacitors and EMI and cosite signal interference solutions. Our products are used in military, space, telecom infrastructure, medical and industrial applications where function and reliability are crucial.